

Title (en)
METHOD AND DEVICE FOR LINING HOLLOW SHAPED PARTS ON THE INTERIOR

Publication
EP 0026945 B1 19830302 (DE)

Application
EP 80200368 A 19800423

Priority
DE 2940188 A 19791004

Abstract (en)
[origin: EP0026945A1] 1. Method for lining hollow shaped parts on the interior, in particular for chimneys or suchlike with a thermal insulating layer of an insulating material, principally of expanded vermiculture and a hydraulic binding agent in which the insulating material is introduced in an annular slot (5) formed between the shaped part (3) and an inner core (4), characterised in that an insulating material with a ratio of water to solid matter of the insulating material of between 1.2 and 2 to 1 is used, that the insulating material is condensed such that it has a gross density of 150 to 400 g/l and/or a compression strength of 0.1 to 1 N/mm**2 and a coefficient of thermal conductivity of $\lambda = 0.18$ to 0.20 W/m . K at an application temperature of 800 degrees to 1000 degrees C, and that the inner core is removed after consolidation and the shaped part is stored up to approximately 48 hours, with drying out being prevented.

IPC 1-7
E04F 17/02

IPC 8 full level
B28B 11/04 (2006.01); **C04B 28/04** (2006.01); **E04F 17/02** (2006.01)

CPC (source: EP)
B28B 11/042 (2013.01); **B28B 11/043** (2013.01); **C04B 28/04** (2013.01); **E04F 17/02** (2013.01)

C-Set (source: EP)
C04B 28/04 + **C04B 14/204** + **C04B 14/38** + **C04B 20/0076** + **C04B 24/383** + **C04B 38/08**

Cited by
EP0072506A1; DE3413192A1; DE3205165A1; EP3239435A1; CZ298380B6; EP1375098A3; EP3239435B1

Designated contracting state (EPC)
AT BE CH FR GB LI LU NL

DOCDB simple family (publication)
EP 0026945 A1 19810415; **EP 0026945 B1 19830302**; AT E2695 T1 19860315; DE 2940188 B1 19810219; DE 2940188 C2 19820715; DK 230980 A 19810405

DOCDB simple family (application)
EP 80200368 A 19800423; AT 80200368 T 19800423; DE 2940188 A 19791004; DK 230980 A 19800528