

Title (en)

METHOD FOR POSTWELD HEAT TREATMENT

Publication

EP 0034057 A3 19811007 (EN)

Application

EP 81300509 A 19810206

Priority

JP 1499780 A 19800209

Abstract (en)

[origin: EP0034057A2] A method for postweld heat treatment (hereinafter referred to as PWHT) for multilayer welding, in which the terminating point of the PWHT is judged correctly to preclude cracking due to insufficient treatment or uneconomical excessive treatment, the method comprising; determining the residual hydrogen concentration directly beneath the final welded layer immediately after completion of welding; determining a crack-preventing critical hydrogen concentration to obtain a ratio of the critical hydrogen concentration to the residual hydrogen concentration; determining the value of a product of a hydrogen diffusivity coefficient during the heat treatment and a holding time where a hydrogen concentration currently occurring in the heat treatment reaches the critical hydrogen concentration, on the basis of the relation of a ratio of the current hydrogen concentration to the residual hydrogen concentration and a sum of a parameter of hydrogen diffusion to be determined depending upon the welding conditions and the above-mentioned product; measuring the temperature of the heat treatment at a suitable point of the weld; and terminating the heat treatment at a time point when a time-integrated value of a hydrogen diffusivity coefficient at the measured temperature exceeds the value of the above-mentioned product.

IPC 1-7

C21D 9/50; C21D 3/06; C21D 11/00

IPC 8 full level

B23K 31/00 (2006.01); **C21D 3/06** (2006.01); **C21D 9/50** (2006.01); **C21D 11/00** (2006.01)

CPC (source: EP)

C21D 3/06 (2013.01); **C21D 9/50** (2013.01); **C21D 11/00** (2013.01)

Citation (search report)

- [A] FR 929700 A 19480105
- [A] FR 2317706 A1 19770204 - BRITISH STEEL CORP [GB]
- WELDING JOURNAL, Vol. 58, No. 52 February 1979 Miami, US W.S. KYTE: "Postweld Heat Treatment for Hydrogen Removal", pages 54s-58s
- METAL TECHNOLOGY, Vol. 2, February 1975, London, GB B. CHEW: "Diffusion of hydrogen in fillet welds", pages 66-72
- [A] STAHL UND EISEN, Vol. 98, No. 22, November 2, 1978 Dusseldorf, DE V. PILOUS: "Temperaturfuhrung beim Schweiessen eines warmfesten Cr-Mo-Ni-V-Stahles mit 0,18%C und 0,92% Cr in grossen Wanddicken", pages 1167-1170.
- [A] STAHL UND EISEN, Vol. 100, No. 1, January 1, 1980 Dusseldorf, DE V. PILOUS: "Beitrag zum Schweiessen eines warmfesten Cr-Mo-Ni-V-Stahles mit 0,18%C und 1% Cr fur Schmiedestucke im Kraftwerksbau" pages 9-12.

Cited by

CN104169035A; WO2013140798A3; USRE48063E

Designated contracting state (EPC)

DE FR IT

DOCDB simple family (publication)

EP 0034057 A2 19810819; EP 0034057 A3 19811007; EP 0034057 B1 19840815; AU 544035 B2 19850516; AU 6696881 A 19810820;
CA 1189427 A 19850625; DE 3165473 D1 19840920; JP S56112421 A 19810904; JP S5856014 B2 19831213

DOCDB simple family (application)

EP 81300509 A 19810206; AU 6696881 A 19810206; CA 370283 A 19810206; DE 3165473 T 19810206; JP 1499780 A 19800209