

Title (en)

CATHODE FOR MOLTEN-SALT ELECTROLYSIS CELL

Publication

EP 0041045 B1 19830622 (DE)

Application

EP 81810185 A 19810515

Priority

CH 403880 A 19800523

Abstract (en)

[origin: ES8203989A1] A solid cathode in a fused salt electrolytic cell for the production of aluminum is made up of individually exchangeable elements (10). These cathode elements are made up of two parts which are rigidly joined together and which are resistant to thermal shock. The upper part (12) which projects from the molten electrolyte (30) into the precipitated aluminum (26), or the coating on this part (12), is made of a material which, at working temperature, is a good electrical conductor, is chemically resistant and is wet by aluminum. The lower part (14,16), which is exclusively in the liquid aluminum (26), or the coating on this part (14,16) is on the other hand made of an insulating material which can withstand molten aluminum.

IPC 1-7

C25C 3/08

IPC 8 full level

C25C 3/08 (2006.01)

CPC (source: EP US)

C25C 3/08 (2013.01 - EP US)

Cited by

FR2508496A2; AU571246B2

Designated contracting state (EPC)

AT CH DE FR GB IT LI NL SE

DOCDB simple family (publication)

EP 0041045 A1 19811202; EP 0041045 B1 19830622; AT E3884 T1 19830715; AU 543106 B2 19850404; AU 7029981 A 19811126; BR 8103210 A 19820216; CA 1163601 A 19840313; DE 3160478 D1 19830728; ES 502372 A0 19820401; ES 8203989 A1 19820401; IS 1170 B6 19841228; IS 2641 A7 19811124; JP S5719391 A 19820201; NO 155104 B 19861103; NO 155104 C 19870211; NO 811711 L 19811124; NZ 197038 A 19840427; US 4376690 A 19830315; YU 132181 A 19830630; ZA 813338 B 19820526

DOCDB simple family (application)

EP 81810185 A 19810515; AT 81810185 T 19810515; AU 7029981 A 19810508; BR 8103210 A 19810522; CA 378173 A 19810522; DE 3160478 T 19810515; ES 502372 A 19810521; IS 2641 A 19810514; JP 7790281 A 19810522; NO 811711 A 19810520; NZ 19703881 A 19810508; US 26204981 A 19810511; YU 132181 A 19810522; ZA 813338 A 19810519