

Title (en)

SEMI-FINISHED STEEL ARTICLE AND METHOD FOR PRODUCING SAME

Publication

**EP 0045815 B1 19840711 (EN)**

Application

**EP 80104708 A 19800811**

Priority

EP 80104708 A 19800811

Abstract (en)

[origin: EP0045815A1] A steel billet is produced having free machining properties and substantially devoid of surface cracking in the as-deformed condition and without surface conditioning. The steel contains bismuth and tellurium and may contain lead but in a smaller amount than is conventional in leaded, free machining steels. The billet was hot deformed at a temperature above about 920 DEG C (1700 DEG F) and below 1150 DEG C (2100 DEG F). The steel contains inclusions of MnTe and Bi<sub>2</sub>Te<sub>3</sub> as well as elemental Bi.

IPC 1-7

**C22C 38/60; C21C 7/00; C21D 7/13**

IPC 8 full level

**C21D 7/13** (2006.01); **C22C 38/60** (2006.01)

CPC (source: EP)

**C21D 7/13** (2013.01); **C22C 38/60** (2013.01)

Citation (examination)

DE 2937908 A1 19800403 - DAIDO STEEL CO LTD

Cited by

GB2191507A; DE3718771A1; GB2191507B

Designated contracting state (EPC)

BE CH DE FR GB IT LI NL

DOCDB simple family (publication)

**EP 0045815 A1 19820217; EP 0045815 B1 19840711; DE 3068522 D1 19840816**

DOCDB simple family (application)

**EP 80104708 A 19800811; DE 3068522 T 19800811**