

Title (en)

METHOD FOR MANUFACTURING A BRAZABLE ALUMINIUM ALLOY.

Title (de)

VERFAHREN ZUR HERSTELLUNG EINER HARTLÖTBAREN ALUMINIUMLEGIERUNG.

Title (fr)

PROCEDE DE FABRICATION D'UN ALLIAGE D'ALUMINIUM BRASABLE.

Publication

**EP 0059742 A1 19820915 (FR)**

Application

**EP 81902622 A 19810909**

Priority

FR 8019876 A 19800911

Abstract (en)

[origin: FR2489845A1] Brazable aluminium alloys, particularly those intended for the manufacturing of heavy machinery. The alloy according to the invention contains in% by weight: Fe: 0.10 to 0.7; Ni: 0.40 to 1.0; Mn: 1.00 to 1.5; Cr0.5; Si: 0.20 to 0.5; Zr0.4; Cu: 0.20 to 0.5; Ti: 0.01 to 0.1; Mg0.5; V0.4; others, each 0.05; total0.15; The balance being aluminium. The production method comprises preferably a homogenization in two steps: (a) in the temperature range from 590°C to 610°C during 2 to 36 hours; (b) in the temperature range from 450°C to 500°C during 30 minutes to 24 hours. The alloy is mainly used for manufacturing large heat exchangers.

Abstract (fr)

L'invention se rapporte aux alliages d'aluminium brasables en particulier a ceux destines a la fabrication de gros appareillages. L'alliage suivant l'invention contient en poids%: Fe 0,10 a 0,7; Ni 0,40 a 1,0; Mn 1,00 a 1,5; Cr (Alpha) 0,5; Si 0,20 a 0,5; Zr (Alpha) 0,4; Cu 0,20 a 0,5; Ti 0,01 a 0,1; Mg (Alpha) 0,5; V (Alpha) 0,4 autres chacun (Alpha) 0,05; total (Alpha) 0,15, reste aluminium. Le procede de fabrication comporte, de preference, une homogeneisation en deux stades. a) dans le domaine de temperature 590 C-610 C pendant 2 a 36 heures b) dans le domaine de temperature 450 C-550 C pendant 30 minutes a 24 heures. L'alliage est principalement utilise a la fabrication de gros echangeurs de chaleur.

IPC 1-7

**C22C 21/00**; **C22F 1/04**; **B23K 35/28**

IPC 8 full level

**C22C 21/00** (2006.01); **C22F 1/04** (2006.01)

CPC (source: EP)

**C22C 21/00** (2013.01)

Designated contracting state (EPC)

AT DE GB NL

DOCDB simple family (publication)

**FR 2489845 A1 19820312**; **FR 2489845 B1 19860606**; BE 890261 A 19820308; CA 1158074 A 19831206; DE 3163515 D1 19840614; EP 0059742 A1 19820915; EP 0059742 B1 19840509; ES 505369 A0 19820816; ES 8206652 A1 19820816; IT 1139424 B 19860924; IT 8123796 A0 19810904; JP S57501385 A 19820805; JP S6050867 B2 19851111; WO 8201014 A1 19820401

DOCDB simple family (application)

**FR 8019876 A 19800911**; BE 205894 A 19810908; CA 385625 A 19810910; DE 3163515 T 19810909; EP 81902622 A 19810909; ES 505369 A 19810910; FR 8100116 W 19810909; IT 2379681 A 19810904; JP 50295781 A 19810909