

Title (en)

METHOD OF PRODUCING PREFORMS OF CADMIUM-FREE SILVER-METAL OXIDE COMPOUND MATERIALS FOR ELECTRIC CONTACTS

Publication

**EP 0080641 B1 19850828 (DE)**

Application

**EP 82110530 A 19821115**

Priority

DE 3146972 A 19811126

Abstract (en)

[origin: US4609525A] The composite according to the invention is prepared by milling an atomized silver, two metal oxide alloy powder dry or wet in a mill in order to reduce its particle size and deform its particle shape. Subsequently an internal oxidation of the powder is carried out in two stages, at a first temperature range between 673 DEG K. and 773 DEG K. for two to six hours and in a second temperature range between 873 DEG K. and 1073 DEG K. for 0.5 to 2 hours. The internally oxidized powder is pressed into molded parts and these are densified by sintering in a temperature range between 973 DEG K. and 1173 DEG K. in air or a neutral atmosphere and by coining.

IPC 1-7

**H01H 11/04; C22C 5/06**

IPC 8 full level

**B22F 1/00** (2006.01); **C22C 1/05** (2006.01); **C22C 5/06** (2006.01); **H01H 1/0237** (2006.01); **H01H 11/04** (2006.01)

CPC (source: EP US)

**H01H 1/02372** (2013.01 - EP US)

Cited by

EP0182386A3; US5134039A; US4565590A

Designated contracting state (EPC)

DE FR GB IT SE

DOCDB simple family (publication)

**EP 0080641 A1 19830608; EP 0080641 B1 19850828**; BR 8206819 A 19831004; DE 3146972 A1 19830601; DE 3265890 D1 19851003; JP S5896801 A 19830609; JP S646259 B2 19890202; US 4609525 A 19860902

DOCDB simple family (application)

**EP 82110530 A 19821115**; BR 8206819 A 19821125; DE 3146972 A 19811126; DE 3265890 T 19821115; JP 20683082 A 19821125; US 79918385 A 19851115