

Title (en)

Corrosion resistant nickel base alloy.

Title (de)

Korrosionsbeständige Legierung auf Nickelbasis.

Title (fr)

Alliage à base de nickel, résistant à la corrosion.

Publication

EP 0091308 A2 19831012 (EN)

Application

EP 83301891 A 19830405

Priority

US 36577982 A 19820405

Abstract (en)

A nickel base alloy is provided having excellent hot and cold workability and superior corrosion resistance to a variety of media including deep sour gas well environments. The alloy consists essentially of 27 to 33% by weight of chromium, 8 to 12% by weight of molybdenum, 0 to 4% by weight of tungsten, up to 1.5% by weight iron, up to 12% by weight of cobalt, up to 0.15% by weight of carbon, up to 1.5% by weight of aluminium, up to 1.5% by weight of titanium, up to 2% by weight of columbium, and the balance nickel.

IPC 1-7

C22C 19/05

IPC 8 full level

C22C 19/05 (2006.01)

CPC (source: EP KR)

C22C 19/05 (2013.01 - KR); **C22C 19/053** (2013.01 - EP)

Cited by

CN104745882A; CN115418529A; GB2390855B; US8414828B2; WO2007023797A1

Designated contracting state (EPC)

AT BE CH DE FR IT LI LU NL SE

DOCDB simple family (publication)

EP 0091308 A2 19831012; EP 0091308 A3 19840905; EP 0091308 B1 19870930; AR 231149 A1 19840928; AT E30050 T1 19871015; AU 1312283 A 19831013; AU 566664 B2 19871029; BR 8301735 A 19831213; CA 1211961 A 19860930; DE 3373921 D1 19871105; GB 2117793 A 19831019; GB 2117793 B 19860416; IN 157179 B 19860201; JP H059503 B2 19930205; JP S58204145 A 19831128; KR 840004180 A 19841010; KR 900007118 B1 19900929; MX 7543 E 19890906; ZA 832119 B 19840425

DOCDB simple family (application)

EP 83301891 A 19830405; AR 29256383 A 19830329; AT 83301891 T 19830405; AU 1312283 A 19830331; BR 8301735 A 19830405; CA 425207 A 19830405; DE 3373921 T 19830405; GB 8309141 A 19830405; IN 369CA1983 A 19830326; JP 5882283 A 19830405; KR 830001288 A 19830330; MX 1057583 U 19830405; ZA 832119 A 19830325