

Title (en)

BLOW LINE ADDITION OF ISOCYANATE BINDER IN FIBERBOARD MANUFACTURE

Publication

EP 0092699 B1 19860903 (EN)

Application

EP 83103332 A 19830406

Priority

US 37189482 A 19820426

Abstract (en)

[origin: US4407771A] A method for producing a synthetic board from cellulosic and/or lignocellulosic materials wherein a polyisocyanate binder is applied to the hot and wet fibrous material in the blow line out of the refiner of the board forming process. Polyphenylpolyisocyanates, such as a mixture of diphenylmethane-4,4'-diisocyanate and polymethylene polyphenyl polyisocyanates, are a particularly suitable binder.

IPC 1-7

B27N 3/00

IPC 8 full level

B27N 1/00 (2006.01); **B27N 3/00** (2006.01); **B27N 3/10** (2006.01); **C08G 18/64** (2006.01); **C08L 97/02** (2006.01)

CPC (source: EP US)

B27N 1/00 (2013.01 - EP US); **B27N 3/002** (2013.01 - EP US); **B27N 3/10** (2013.01 - EP US); **C08G 18/6484** (2013.01 - EP US); **C08L 97/02** (2013.01 - EP US)

Cited by

DE4312564A1; AT403023B; EP0821749A4; EP0562219A1; EP0559880A4; EP0515875A1; EP0173866A1; DE102008023007A1; DE102007054123A1; WO9423914A1; WO9623637A1

Designated contracting state (EPC)

DE FR GB IT SE

DOCDB simple family (publication)

EP 0092699 A2 19831102; **EP 0092699 A3 19840711**; **EP 0092699 B1 19860903**; AU 1073683 A 19831103; AU 549980 B2 19860220; CA 1174422 A 19840918; DE 3365799 D1 19861009; JP S58194529 A 19831112; US 4407771 A 19831004

DOCDB simple family (application)

EP 83103332 A 19830406; AU 1073683 A 19830125; CA 419773 A 19830119; DE 3365799 T 19830406; JP 7366083 A 19830426; US 37189482 A 19820426