

Title (en)

ROTARY HEARTH FURNACE FOR THERMIC, THERMOCHEMICAL OR ELECTROTHERMIC TREATMENT OF METALS IN A DILUTED ATMOSPHERE

Publication

EP 0093060 B1 19860903 (FR)

Application

EP 83400814 A 19830425

Priority

FR 8207224 A 19820427

Abstract (en)

[origin: EP0093060A1] 1. A rotary hearth furnace for thermic, thermochemical or electrothermic treatment of metal parts in a diluted atmosphere characterized in that it comprises : - a sealed metal enclosure (1), which may include a double wall, with an interposed cooling layer, this enclosure (1) comprising a side wall (2) preferably having a circular horizontal section, a cover (3) and a bottom (4) - means for creating, within the enclosure, an atmosphere for treatment under reduced pressure ; - a circular rolling path provided inside the enclosure on said bottom, in a peripheral region substantially adjacent the cylindrical wall ; - an annular tunnel (12) made of a heat isolating material, situated above the rolling track, this tunnel being open on its lower surface opposite the rolling track, this tunnel including means (13) for thermic, thermochemical or electrothermic treatment ; - a rotary hearth (22) consisting of a ring made of a heat isolating material, this hearth being movable on the rolling track and arranged so as to close the aperture of the lower part of the tunnel and thus provide continuity of the thermic isolation of the tunnel (12) as far as its lower surface is concerned ; - means for rotating the rotary hearth (22) by a motor (24) preferably lodged outside the enclosure ; - elements for supporting the parts (S) evenly distributed on the rotary hearth (22) ; - a hardening cell, comprising, on the one hand, a chamber forming a lock (6), also serving for charging and discharging the parts to be treated, this chamber being mounted against the side wall (2), inside the enclosure and communicating with the inner volume of the tunnel (12) by a first door and, if need be, a movable separating wall, and with the outside by a second door so as to allow the introduction and discharge of the parts to be treated inside the tunnel, and, on the other hand, a hardening a hardening vat (9) lodged below said chamber (6), this hardening cell comprising handling means (10) for depositing the parts on or taking them away from the rotary hearth, and for plunging them, at the end of treatment, into the hardening vat (9).

IPC 1-7

F27B 9/16; **C21D 1/76**; **F27B 9/04**

IPC 8 full level

C21D 1/76 (2006.01); **C21D 1/773** (2006.01); **F27B 9/04** (2006.01); **F27B 9/16** (2006.01)

CPC (source: EP)

C21D 1/773 (2013.01); **F27B 9/042** (2013.01); **F27B 9/16** (2013.01)

Cited by

CN104864721A; CN112985052A; EP0272353A1; US4813381A; CN110514017A; US8298474B2; WO2009121326A3; WO2009047211A1; WO2009100791A1

Designated contracting state (EPC)

AT BE CH DE GB IT LI LU NL SE

DOCDB simple family (publication)

EP 0093060 A1 19831102; **EP 0093060 B1 19860903**; AT E21967 T1 19860915; DE 3365808 D1 19861009; FR 2525751 A1 19831028; FR 2525751 B1 19840817

DOCDB simple family (application)

EP 83400814 A 19830425; AT 83400814 T 19830425; DE 3365808 T 19830425; FR 8207224 A 19820427