

Title (en)

METHOD AND ALLOY FOR THE HOT DIP GALVANIZING OF SILICON STEEL, AND GALVANIZED ARTICLES

Publication

EP 0095402 B1 19870401 (FR)

Application

EP 83400916 A 19830505

Priority

FR 8207772 A 19820505

Abstract (en)

[origin: ES8405849A1] Disclosed herein is an alloy for galvanizing object of steel which have a concentration of silicon lower than 0.45% by weight. The alloy consists essentially of 0.5 to 1.5% by weight of lead, 0.005 to 0.2% by weight of germanium and the balance zinc. The alloy may further contain 0.001 to 0.05% by weight aluminum.

IPC 1-7

C22C 18/00; C23C 2/06

IPC 8 full level

C22C 18/00 (2006.01); **C23C 2/06** (2006.01)

CPC (source: EP US)

C22C 18/00 (2013.01 - EP US); **C23C 2/06** (2013.01 - EP US); **Y10T 428/12799** (2015.01 - EP US)

Citation (examination)

Le Zinc, sa métallurgie, ses applications, pages 29-30, 72, Centre technique du Zinc, 1968

Designated contracting state (EPC)

AT BE CH DE FR GB IT LI LU NL SE

DOCDB simple family (publication)

EP 0095402 A1 19831130; EP 0095402 B1 19870401; AT E26308 T1 19870415; CA 1193154 A 19850910; DE 3370654 D1 19870507; ES 522090 A0 19840616; ES 8405849 A1 19840616; FR 2526445 A1 19831110; FR 2526445 B1 19840907; GR 79280 B 19841022; JP S58207363 A 19831202; US 4636354 A 19870113; US 4699815 A 19871013

DOCDB simple family (application)

EP 83400916 A 19830505; AT 83400916 T 19830505; CA 427393 A 19830504; DE 3370654 T 19830505; ES 522090 A 19830504; FR 8207772 A 19820505; GR 830171296 A 19830504; JP 7888983 A 19830504; US 59234784 A 19840322; US 93804186 A 19861204