

Title (en)

Composite material having improved bond strength and process for making the same.

Title (de)

Verbundwerkstoff mit erhöhter Haftfestigkeit und Verfahren zu seiner Herstellung.

Title (fr)

Matériau composite à adhérence améliorée et procédé pour sa fabrication.

Publication

EP 0098139 A2 19840111 (EN)

Application

EP 83303698 A 19830627

Priority

US 39299982 A 19820628

Abstract (en)

A composite material having improved bond strength and a substantially smooth external surface comprises a deoxidized copper alloy core material and a copper-aluminium-silicon clad material. The composite is formed by rolling together the core and clad, preferably in an unheated condition, in a single pass with a reduction of about 50% to 75% to form a metallurgical bond between the core and clad and thereafter enhancing the bond strength by heating the bonded core and cladding to a temperature in the range of about 200°C to about 750°C for a time period of about 5 minutes to about 24 hours.

IPC 1-7

B32B 15/01; B23K 20/04

IPC 8 full level

B23K 20/00 (2006.01); **B23K 20/233** (2006.01); **B32B 15/01** (2006.01); **C22C 1/00** (2006.01); **C22C 9/00** (2006.01); **C22F 1/08** (2006.01); **H05K 1/05** (2006.01)

CPC (source: EP US)

B23K 20/233 (2013.01 - EP US); **B32B 15/01** (2013.01 - EP US); **H05K 1/05** (2013.01 - EP US); **Y10S 428/94** (2013.01 - EP US); **Y10T 428/1291** (2015.01 - EP US)

Cited by

EP0917951A1

Designated contracting state (EPC)

DE FR GB IT NL SE

DOCDB simple family (publication)

EP 0098139 A2 19840111; EP 0098139 A3 19850109; CA 1200953 A 19860225; JP S5919088 A 19840131; US 4429022 A 19840131

DOCDB simple family (application)

EP 83303698 A 19830627; CA 426441 A 19830421; JP 11575283 A 19830627; US 39299982 A 19820628