

Title (en)
RECOMPRESSION PROCESS

Publication
EP 0118480 B1 19871202 (DE)

Application
EP 83902690 A 19830901

Priority
CH 525882 A 19820903

Abstract (en)
[origin: WO8400982A1] Anodized metal surfaces are cold pressed while they are treated at a temperature lower than 30°C in a still wet state with an aqueous solution containing nickel salt and at least one fluoride. The solution may contain further additives for example a preserving agent, optionally dissolved in a solubilization agent such as alcohols.

IPC 1-7
C25D 11/24

IPC 8 full level
C25D 11/24 (2006.01)

CPC (source: EP US)
C25D 11/246 (2013.01 - EP US)

Citation (examination)
EP 0101820 A1 19840307 - ITALTECNO SRL [IT]

Cited by
DE102007005073A1

Designated contracting state (EPC)
AT BE CH DE FR GB LI LU NL SE

DOCDB simple family (publication)
WO 8400982 A1 19840315; DE 3374791 D1 19880114; EP 0118480 A1 19840919; EP 0118480 B1 19871202; US 4648911 A 19870310

DOCDB simple family (application)
CH 8300100 W 19830901; DE 3374791 T 19830901; EP 83902690 A 19830901; US 61099684 A 19840501