

Title (en)  
LINING FOR AN ELECTROLYTIC CELL FOR THE PRODUCTION OF ALUMINIUM

Publication  
**EP 0132647 B1 19870304 (DE)**

Application  
**EP 84107810 A 19840705**

Priority  
DE 3327230 A 19830728

Abstract (en)  
[origin: US4589967A] Cell for the fusion-electrolytic production of aluminum which consists of a steel shell lined with graphite blocks, a heat-retarding insulation layer between the shell and the lining and cathodic bus bars inserted into the lining. Features of the invention are (a) the lining consists of graphite blocks with a heat conductivity of 80 to 120 W/mxK, an electric resistivity from 6 to 13 mu OMEGA m and an accessible pore volume of at most 22%, (b) the insulating layer contains at least two partial layers with a heat conductivity of 0.1 to 0.2 and 0.8 to 1.2 W/mxK, (c) the thickness ratio of the lining and the insulating layer is 1.5 to 3.0.

IPC 1-7  
**C25C 3/08**

IPC 8 full level  
**C25C 3/08** (2006.01)

CPC (source: EP US)  
**C25C 3/08** (2013.01 - EP US); **C25C 3/085** (2013.01 - EP US)

Cited by  
FR2900665A1; US8440059B2; US6627062B1; US6723212B1; WO2007125195A3; KR101217901B1; EP1159469B1; EP1159469A1

Designated contracting state (EPC)  
CH FR GB LI NL

DOCDB simple family (publication)  
**EP 0132647 A2 19850213; EP 0132647 A3 19850313; EP 0132647 B1 19870304**; AU 3086284 A 19850131; AU 565836 B2 19871001; CA 1248495 A 19890110; DE 3327230 A1 19850207; DE 3327230 C2 19900823; JP S6052589 A 19850325; NO 161008 B 19890313; NO 161008 C 19890621; NO 842315 L 19850129; US 4589967 A 19860520

DOCDB simple family (application)  
**EP 84107810 A 19840705**; AU 3086284 A 19840719; CA 458820 A 19840713; DE 3327230 A 19830728; JP 15713884 A 19840727; NO 842315 A 19840608; US 62880784 A 19840709