

Title (en)
ALUMINA-ZIRCONIA ABRASIVE

Publication
EP 0140164 B1 19870429 (EN)

Application
EP 84111499 A 19840926

Priority
US 53721483 A 19830929

Abstract (en)
[origin: US4457767A] Abrasive properties of co-fused alumina zirconia are improved by the addition of from 0.1 to 2% of Y2O3 to the fusion mix and quenching the fused product. Y2O3 ores containing mostly Y2O3 with lesser amounts of rare earth oxides can be substituted for high purity Y2O3.

IPC 1-7
C09K 3/14

IPC 8 full level
B24D 3/00 (2006.01); **C04B 35/10** (2006.01); **C04B 35/653** (2006.01); **C09K 3/14** (2006.01)

CPC (source: EP US)
C04B 35/109 (2013.01 - EP US); **C04B 35/117** (2013.01 - EP US); **C04B 35/484** (2013.01 - EP US); **C04B 35/4885** (2013.01 - EP US); **C04B 35/62204** (2013.01 - EP US); **C04B 35/62665** (2013.01 - EP US); **C04B 35/653** (2013.01 - EP US); **C09K 3/1427** (2013.01 - EP US); **C04B 2235/3206** (2013.01 - EP US); **C04B 2235/3208** (2013.01 - EP US); **C04B 2235/3224** (2013.01 - EP US); **C04B 2235/3225** (2013.01 - EP US); **C04B 2235/3227** (2013.01 - EP US); **C04B 2235/3229** (2013.01 - EP US); **C04B 2235/3232** (2013.01 - EP US); **C04B 2235/3272** (2013.01 - EP US); **C04B 2235/402** (2013.01 - EP US); **C04B 2235/785** (2013.01 - EP US)

Cited by
EP0495662A1

Designated contracting state (EPC)
AT CH DE FR GB IT LI SE

DOCDB simple family (publication)
US 4457767 A 19840703; AT E26855 T1 19870515; AU 3353684 A 19850404; AU 573625 B2 19880616; BR 8404844 A 19850813; CA 1207153 A 19860708; DE 3463393 D1 19870604; EP 0140164 A1 19850508; EP 0140164 B1 19870429; ES 536206 A0 19850716; ES 8506782 A1 19850716; IN 162220 B 19880416; JP H0312597 B2 19910220; JP S6099567 A 19850603; ZA 847230 B 19851127

DOCDB simple family (application)
US 53721483 A 19830929; AT 84111499 T 19840926; AU 3353684 A 19840926; BR 8404844 A 19840926; CA 453779 A 19840508; DE 3463393 T 19840926; EP 84111499 A 19840926; ES 536206 A 19840925; IN 662CA1984 A 19840920; JP 15948984 A 19840731; ZA 847230 A 19840913