

Title (en)

ZINC OXIDE VARISTOR

Publication

EP 0147607 B1 19880504 (DE)

Application

EP 84113877 A 19841116

Priority

CH 685183 A 19831222

Abstract (en)

[origin: US4559167A] A varistor of metal oxides, predominantly zinc oxide (ZnO), is provided on its lateral surface between two contact faces, with a coating consisting at least partially of an organic polymer. In order to prevent rapid degradation in oxygen-free surroundings, the coating contains at least one oxygen barrier layer or is formed entirely as such a layer, which contains filler particles in an organic matrix material. The filler is here taken from the group comprising the following substances or groups of substances: synthetic mica, natural mica, vermiculite, micaceous iron ore, glass and other non-metallic inorganic substances present in the form of platelets or flakes; metal oxides, active part material in a pulverulent form and other oxygen-releasing inorganic substances. The organic matrix material is selected from the group comprising epoxide resins, alkyd resins, polyurethanes, silicone resins, unsaturated polyester resins and acrylates. The oxygen barrier layer or layers can be formed by a coating consisting of a band with a carrier of paper, plastic or glass fabric, the band being wound once or several times around the active part.

IPC 1-7

H01C 7/10

IPC 8 full level

H01C 7/10 (2006.01); **H01C 7/102** (2006.01)

CPC (source: EP US)

H01C 7/102 (2013.01 - EP US); **Y10T 428/31609** (2015.04 - EP US); **Y10T 428/31663** (2015.04 - EP US); **Y10T 428/31786** (2015.04 - EP US)

Cited by

EP0452511A4; EP0620567A1; EP0217021A1; US4805064A

Designated contracting state (EPC)

CH DE GB LI SE

DOCDB simple family (publication)

EP 0147607 A1 19850710; EP 0147607 B1 19880504; DE 3470975 D1 19880609; JP S60158603 A 19850820; US 4559167 A 19851217

DOCDB simple family (application)

EP 84113877 A 19841116; DE 3470975 T 19841116; JP 26760084 A 19841220; US 67630384 A 19841129