

Title (en)
AMORPHOUS TRANSITION METAL ALLOY, THIN GOLD COATED, ELECTRICAL CONTACT

Publication
EP 0160761 B1 19890208 (EN)

Application
EP 84303633 A 19840530

Priority
US 60913784 A 19840511

Abstract (en)
[origin: EP0160761A1] An electrical contact, and a method of forming an electrical contact, result in a structure that may utilize far less gold than conventional electrical contacts while having the same, or superior, desirable properties. The electrical contact includes an electrically conductive substrate with an amorphous transition metal alloy electrolytically deposited on the substrate. The amorphous transition metal alloy is a nickel phosphorus, or nickel cobalt phosphorus alloy, and has an uncovered coating of gold thereover. The gold coating is between about 1-30 microinches thick, preferably 5-15 microinches of hard gold.

IPC 1-7
C25D 3/56; **C25D 5/10**; **C25D 7/00**; **H01H 1/02**

IPC 8 full level
H01H 11/04 (2006.01); **C25D 3/56** (2006.01); **C25D 5/10** (2006.01); **C25D 7/00** (2006.01); **H01H 1/02** (2006.01); **H01H 1/021** (2006.01); **H01H 1/04** (2006.01)

CPC (source: EP US)
C25D 3/562 (2013.01 - EP); **C25D 5/10** (2013.01 - EP US); **C25D 5/619** (2020.08 - EP US); **H01H 1/021** (2013.01 - EP)

Cited by
US5408574A; US5637925A; EP0384579A1; EP1086807A3; EP2753731A4; DE3838971A1; GB2212516A; US5468936A; US5066550A; US2014234663A1; US9765438B2; WO2017066344A1; US8857468B2; US7615255B2; EP0410472A2; WO2017066342A1; WO03050920A1; WO2007039302A1; EP0410472B1

Designated contracting state (EPC)
AT BE CH DE FR GB IT LI LU NL SE

DOCDB simple family (publication)
EP 0160761 A1 19851113; **EP 0160761 B1 19890208**; AT E40721 T1 19890215; DE 3476684 D1 19890316; ES 533300 A0 19851016; ES 8601557 A1 19851016; JP S6129021 A 19860208

DOCDB simple family (application)
EP 84303633 A 19840530; AT 84303633 T 19840530; DE 3476684 T 19840530; ES 533300 A 19840611; JP 11217484 A 19840531