

Title (en)
PROCESS FOR MAKING HIGH-POWER GRAPHITE ELECTRODES

Publication
EP 0177981 B1 19881109 (DE)

Application
EP 85200993 A 19850624

Priority
DE 3432887 A 19840907

Abstract (en)
[origin: EP0177981A1] 1. A process for making high-power graphite electrodes from two components in the form of anisotropic needle cokes and an electrode binder on the basis of coal tar pitch, which has a proportion of beta-resins of more than 20% by weight and a quinoline-insoluble content (QI) of more than 5% by weight, which process comprises the steps of mixing the two components, moulding the green electrode and burning and graphitizing the electrode, characterized in that 70 to 80 parts by weight of an anisotropic needle coke are mixed homogeneously with 20 to 30 parts by weight of the binder, which has an atomic C/H ratio of the quinoline-insoluble of a maximum of 3 : 1, an ash value of 0.1% by weight or less and a softening point of 80 to 120 degrees C.

IPC 1-7
H05B 7/085; **C10B 55/00**

IPC 8 full level
C10B 55/00 (2006.01); **H05B 7/085** (2006.01)

CPC (source: EP)
H05B 7/085 (2013.01)

Cited by
AT515982A1; AT515982B1

Designated contracting state (EPC)
DE FR GB IT NL

DOCDB simple family (publication)
EP 0177981 A1 19860416; **EP 0177981 B1 19881109**; DE 3432887 A1 19860320; DE 3566209 D1 19881215

DOCDB simple family (application)
EP 85200993 A 19850624; DE 3432887 A 19840907; DE 3566209 T 19850624