

Title (en)

METHOD FOR PRODUCING HIGH STRENGTH STEEL WITH GOOD DUCTILITY

Publication

**EP 0179952 B1 19880914 (EN)**

Application

**EP 84201584 A 19841030**

Priority

EP 84201584 A 19841030

Abstract (en)

[origin: EP0179952A1] The present invention provides a method for producing hot rolled steel products having high strength and ductility. The method is particularly suitable for low alloy structural steels, which contain about 0.02 to 0.15 wt % C and 0.100 to about .015 % Nb, the higher Nb percentage being used for steels with the lower C content and vice versa. In the method, the steel is heated to a temperature of about 1150 to about 1250 DEG C. The steel is then rolled during a first sequence of passes so that the average austenite grain size at the end of the first sequence stays below about 50 mu m and so that the last pass in this sequence is conducted within the temperature range of about 950 to 1100 DEG C. In a second rolling sequence directly following the first sequence, the rolling is continued with further reductions that do not exceed about 15% in each pass. Subsequently, the steel may be cooled to ambient temperature in a conventional manner.

IPC 1-7

**C21D 8/02**; **C21D 7/13**

IPC 8 full level

**C21D 7/13** (2006.01); **C21D 8/02** (2006.01)

CPC (source: EP)

**C21D 7/13** (2013.01); **C21D 8/0226** (2013.01)

Designated contracting state (EPC)

AT BE DE FR GB LU NL

DOCDB simple family (publication)

**EP 0179952 A1 19860507**; **EP 0179952 B1 19880914**; AT E37202 T1 19880915; DE 3474042 D1 19881020

DOCDB simple family (application)

**EP 84201584 A 19841030**; AT 84201584 T 19841030; DE 3474042 T 19841030