

Title (en)

BATH FOR THE GALVANIC DEPOSITION OF GOLD-TIN ALLOY COATINGS

Publication

**EP 0194432 B1 19880615 (DE)**

Application

**EP 86101083 A 19860128**

Priority

DE 3509367 A 19850315

Abstract (en)

[origin: US4634505A] To produce electrolytic deposition of glossy gold/tin alloys there are employed baths having a pH below 3 which contain 1 to 20 g/l gold in the form of tetracyanoaurate (III), 0.1 to 10 g/l tin, an acid and a conducting salt, whereby the tin is in the form of a tin (IV)-oxalato complex.

IPC 1-7

**C25D 3/62**

IPC 8 full level

**C25D 3/62** (2006.01)

CPC (source: EP US)

**C25D 3/62** (2013.01 - EP US)

Designated contracting state (EPC)

BE CH DE FR GB IT LI

DOCDB simple family (publication)

**DE 3509367 C1 19860814**; BR 8601029 A 19861125; DE 3660313 D1 19880721; EP 0194432 A1 19860917; EP 0194432 B1 19880615; HK 58191 A 19910802; JP H0684553 B2 19941026; JP S61223194 A 19861003; US 4634505 A 19870106; ZA 86309 B 19860827

DOCDB simple family (application)

**DE 3509367 A 19850315**; BR 8601029 A 19860311; DE 3660313 T 19860128; EP 86101083 A 19860128; HK 58191 A 19910725; JP 5518786 A 19860314; US 83322886 A 19860226; ZA 86309 A 19860115