

Title (en)

MULTILAYERED AND HIGHLY WEAR-RESISTANT PROTECTIVE COATING OF HARD MATERIAL FOR METALLIC SURFACES OR SUBSTRATES SUBJECTED TO A HIGH LOAD

Publication

EP 0197185 A3 19880330 (DE)

Application

EP 85109800 A 19850805

Priority

DE 3512986 A 19850411

Abstract (en)

[origin: US4835062A] A protective coating for metallic substrates consists of a plurality of layers having a total thickness ranging from 0.1 to 10 μ , an individual thickness for each layer ranging from 0.5 to 40 nm, and a total number of layers which does not exceed 20,000, each layer being comprised of one kind of at least two kinds of crystalline hard substances and being arranged in a sequentially alternating order with respect to the others, the crystalline hard substances having phase interfaces with respect to one another which are at least crystallographically partially coherent. In an alternate embodiment, the protective coating is a single layer which is a superfinely dispersed mixture of the crystalline hard substances. The multi-layered embodiment is provided by a method which includes positioning the metallic substrate in a physical vapor deposition apparatus; providing at least two cathodes in the apparatus, each cathode being comprised of a different kind of crystalline hard substance; continuously moving the metallic substrate sequentially past each cathode; and causing the vapor deposition of the crystalline hard substances on the metallic substrate as a protective coating having a plurality of layers. The single-layered embodiment is provided by an alternate method in which one cathode is provided and is comprised of at least two kinds of crystalline hard substances. These protective coatings have a resistance to wear which exceeds that for a coating comprised of any one of the crystalline hard substances alone.

IPC 1-7

C23C 28/04; **C23C 14/00**

IPC 8 full level

C23C 14/06 (2006.01); **C23C 14/00** (2006.01); **C23C 28/04** (2006.01)

CPC (source: EP US)

C23C 28/044 (2013.01 - EP US)

Citation (search report)

- [A] DE 1954366 B1 19710624 - HERAEUS GMBH W C [DE]
- [A] DE 1951362 A1 19710616 - HERAEUS GMBH W C
- [A] FR 2276133 A1 19760123 - PLANSEE METALLWERK [AT]
- [A] FR 2282483 A1 19760319 - PLANSEE METALLWERK [AT]
- [A] DE 3112460 A1 19820930 - KRUPP GMBH [DE]
- [A] GB 2045810 A 19801105 - NL VINTAGE
- [A] FR 2378204 A1 19780818 - SUISSE HORLOGERIE RECH LAB [CH]
- [A] EP 0006534 A1 19800109 - STELLRAM SA [CH]
- [A] US 4060471 A 19771129 - PINCH HARRY LOUIS, et al
- [A] THIN SOLID FILMS, Band 54, Nr. 1, Oktober 1978, Seiten 85-106, Elsevier Sequoia S.A., Lausanne, CH; R.F. BUNSHAH et al.: "Structure and properties of refractory compounds deposited by electron beam evaporation"
- [A] THIN SOLID FILMS, Band 118, Nr. 3, August 1984, Seiten 293-299, Elsevier Sequoia, Lausanne, CH; R.C. BUDHANI et al.: "Microstructure and mechanical properties of TiC-Al₂O₃ coatings"
- [A] PATENT ABSTRACTS OF JAPAN, Band 8, Nr. 93 (C-220)[1530], 27. April 1984; & JP-A-59 009 169 (RICOH K.K.) 18-01-1984

Cited by

EP0701982A1; US5700551A; AT16481U1; US6395379B1; WO9322746A1; WO9810120A1

Designated contracting state (EPC)

AT FR GB SE

DOCDB simple family (publication)

EP 0197185 A2 19861015; **EP 0197185 A3 19880330**; **EP 0197185 B1 19900516**; AT E52815 T1 19900615; DE 3512986 A1 19861016; DE 3512986 C2 19880204; JP H0580547 B2 19931109; JP S61235555 A 19861020; US 4835062 A 19890530

DOCDB simple family (application)

EP 85109800 A 19850805; AT 85109800 T 19850805; DE 3512986 A 19850411; JP 8029086 A 19860409; US 83662886 A 19860305