

Title (en)

METHOD AND USE OF A STEEL FOR MANUFACTURING STEEL PIPES WITH A HIGH RESISTANCE TO ACID GASES

Publication

EP 0205828 B1 19891018 (DE)

Application

EP 86105810 A 19860426

Priority

DE 3520702 A 19850610

Abstract (en)

[origin: US4721536A] For increasing the resistance of steel pipes or tubes against acidic medium, by a combination of a heat treatment and the use of an alloyed steel, a compressure stress is built up on the side of the tubes or pipes facing the acidic medium, of up to 30% of the yield limit.

IPC 1-7

C21D 9/14; **C21D 9/50**; **C22C 38/00**

IPC 8 full level

C21D 8/10 (2006.01); **B23K 9/23** (2006.01); **C21D 9/14** (2006.01); **C21D 9/50** (2006.01); **C22C 38/00** (2006.01); **C22C 38/54** (2006.01)

CPC (source: EP US)

C21D 9/14 (2013.01 - EP US); **C21D 9/50** (2013.01 - EP US)

Citation (examination)

DIN 17172 (Mai 1978)

Cited by

CN106180981A; EP0674013A3; US5817275A; US5181974A; US5192376A; FR2764669A1; EP0356417A1; EP0295500A1; WO9857085A1

Designated contracting state (EPC)

AT BE CH DE FR GB IT LI LU NL SE

DOCDB simple family (publication)

EP 0205828 A1 19861230; **EP 0205828 B1 19891018**; AT E47428 T1 19891115; CA 1258571 A 19890822; DE 3666461 D1 19891123; JP S6254022 A 19870309; US 4721536 A 19880126

DOCDB simple family (application)

EP 86105810 A 19860426; AT 86105810 T 19860426; CA 511222 A 19860610; DE 3666461 T 19860426; JP 13292686 A 19860610; US 87240586 A 19860610