

Title (en)

BIAXIALLY ORIENTED COEXTRUDED OPAQUE FOIL

Publication

EP 0220619 A3 19880928 (DE)

Application

EP 86114370 A 19861017

Priority

DE 3538101 A 19851026

Abstract (en)

[origin: EP0220619A2] Coextrusion of the melt of a polypropylene base layer and the melt of top layers gives a multilayer film having a density of less than or equal to 0.75 g/cm³, at least one of the top layers applied on both sides of the base layer being cold- or heat-sealable. At least one of the top layers is readily printable without pretreatment of the multilayer film by corona discharge being necessary. The printable top layer comprises a copolyester in the form of polycondensates from terephthalic acid, isophthalic acid and ethylene glycol or butanediol. If only top layer comprises a copolyester, the other , opposite top layer is a heat-sealable polyolefinic heat-sealing raw material.

IPC 1-7

B32B 27/32

IPC 8 full level

B32B 27/32 (2006.01)

CPC (source: EP US)

B32B 27/08 (2013.01 - US); **B32B 27/20** (2013.01 - US); **B32B 27/32** (2013.01 - EP US); **B32B 27/36** (2013.01 - US);
B32B 2307/31 (2013.01 - US); **B32B 2307/41** (2013.01 - US); **B32B 2307/518** (2013.01 - US); **B32B 2323/10** (2013.01 - US);
B32B 2553/00 (2013.01 - US)

Citation (search report)

- [APD] EP 0177872 A2 19860416 - HOECHST AG [DE]
- [A] GB 1453621 A 19761027 - TOYO SEIKAN KAISHA LTD
- [A] DE 2402120 A1 19740801 - MINNESOTA MINING & MFG

Cited by

EP1658973A1; US5762840A; EP0860271A1; US5529843A; US5932157A; EP0418836A3; US5324467A; EP0367613A3; GB2224973A;
GB2224973B; GB2479561A; GB2479561B; US8142893B2; US8449984B2

Designated contracting state (EPC)

BE DE FR GB IT NL

DOCDB simple family (publication)

EP 0220619 A2 19870506; EP 0220619 A3 19880928; EP 0220619 B1 19910925; DE 3538101 A1 19870430; DE 3681686 D1 19911031

DOCDB simple family (application)

EP 86114370 A 19861017; DE 3538101 A 19851026; DE 3681686 T 19861017