

Title (en)  
Process for producing a polyarylene sulfide.

Title (de)  
Verfahren zur Herstellung von Polyarylensulfid.

Title (fr)  
Procédé pour préparer un polyarylène sulfure.

Publication  
**EP 0226909 A2 19870701 (EN)**

Application  
**EP 86116909 A 19861204**

Priority  
JP 28301785 A 19851218

Abstract (en)  
[origin: JPS62143932A] PURPOSE:To obtain polyphenylene sulfide with small content of heavy metals and outstanding electrical properties and thermal stability by polymerization between a polyhalogenated aromatic compound and reaction product derived from mixing alkali metal sulfide, water and organic polar solvent in specified proportion followed by heating and dehydration. CONSTITUTION:The objective polyphenylene sulfide can be obtained by polymerization, pref. at 200-270 deg.C for 0.5-20hr under stirring between (A) a reaction product derived from mixing (1) an alkali metal sulfide (e.g. lithium sulfide) (2) water and (3) an organic polar solvent (pref. N,N'-dimethyl acetamide) in a molar ratio (1):(2):(3)=1:10-20:1-10 followed by heating (pref. to 100-230 deg.C) and dehydration (pref. to a point of the molar ratio of the alkali metal sulfide to the water falling between 1 and 0.9-2.0) and (B) a polyhalogenated aromatic compound (e.g. p-dichlorobenzene). USE:Films, sheets, etc.

IPC 1-7  
**C08G 75/02**

IPC 8 full level  
**C08G 75/02** (2016.01); **C08G 75/0254** (2016.01); **C08G 75/06** (2006.01)

CPC (source: EP US)  
**C08G 75/0231** (2013.01 - EP US); **C08G 75/025** (2013.01 - EP US)

Cited by  
EP0280274A3; EP0353716A3; EP0302218A1; US5155207A; EP0456349A3; EP0480685A3; EP0280271A3; US11274183B2; WO2019059593A1; US10731006B2; US10800884B2; US11203665B2

Designated contracting state (EPC)  
DE FR GB IT

DOCDB simple family (publication)  
**EP 0226909 A2 19870701**; **EP 0226909 A3 19880420**; **EP 0226909 B1 19920325**; CA 1274047 A 19900911; DE 3684569 D1 19920430; JP H0649761 B2 19940629; JP S62143932 A 19870627; US 4794161 A 19881227

DOCDB simple family (application)  
**EP 86116909 A 19861204**; CA 524943 A 19861210; DE 3684569 T 19861204; JP 28301785 A 19851218; US 94300986 A 19861218