

Title (en)

PROCESS OD DESENSITIZATION TO EXFOLIATING CORROSION OF LITHIUM-CONTAINING ALUMINIUM ALLOYS, RESULTING SIMULTANEOUSLY IN A HIGH MECHANICAL RESISTANCE AND IN GOOD DAMAGE LIMITATION

Publication

**EP 0227563 B1 19900418 (FR)**

Application

**EP 86420293 A 19861126**

Priority

FR 8518208 A 19851128

Abstract (en)

[origin: EP0227563A1] 1. A process for the heat treatment of Al alloys containing Li to improve their resistance to exfoliation corrosion while retaining a high level of mechanical strength and good resistance to damage characterised in that the final ageing operation is carried out in the following range of temperatures T (in degree C) and times t (in hours) :  $t \geq 24 \times 5 \exp((150-T)/30)$   $t \leq 80 \times 5 \exp((150-T)/30)$  with : T  $\leq 160$  degrees C for Mg  $\geq 2\%$  T  $\leq 160$  degrees C-5 (2-% Mg) degrees C for 1  $\leq$  Mg  $\leq 2\%$  T  $\leq 155$  degrees C for Mg  $\leq 1\%$ .

IPC 1-7

**C22F 1/047**; **C22F 1/057**

IPC 8 full level

**C22F 1/00** (2006.01); **C22F 1/04** (2006.01); **C22F 1/047** (2006.01); **C22F 1/057** (2006.01)

CPC (source: EP)

**C22F 1/047** (2013.01); **C22F 1/057** (2013.01)

Citation (examination)

EP 0214381 A1 19870318 - BOEING CO [US]

Cited by

US5198045A; US5240521A; US5133931A; US5211910A; GB2262744A; GB2262744B; EP0571542A4; FR2675816A1; FR2945464A1; CN102421563A; US5462712A; US5259897A; WO2010130887A1; US8118950B2; US9587294B2; US8469255B2; US9555504B2

Designated contracting state (EPC)

AT BE CH DE ES FR GB IT LI NL SE

DOCDB simple family (publication)

**EP 0227563 A1 19870701**; **EP 0227563 B1 19900418**; AT E52109 T1 19900515; BR 8605809 A 19870825; CA 1291927 C 19911112; DE 3670510 D1 19900523; ES 2014248 B3 19900701; IL 80765 A0 19870227; JP S62142752 A 19870626

DOCDB simple family (application)

**EP 86420293 A 19861126**; AT 86420293 T 19861126; BR 8605809 A 19861127; CA 523887 A 19861126; DE 3670510 T 19861126; ES 86420293 T 19861126; IL 8076586 A 19861126; JP 28302486 A 19861127