

Title (en)

ORGANIC COATED STEEL STRIP HAVING IMPROVED BAKE HARDENABILITY AND METHOD FOR MAKING

Publication

EP 0230320 B1 19910130 (EN)

Application

EP 87100847 A 19870122

Priority

- JP 1322986 A 19860124
- JP 29003586 A 19861205

Abstract (en)

[origin: EP0230320A1] An organic coated steel strip having improved bake hardenability is provided which comprises an extra low carbon-steel substrate having bake hardenability, a zinc alloy layer deposited on the substrate in a weight of 10 to 40 g/m², a chromate layer formed on the zinc alloy layer in a weight of at least 10 mg/m² of metallic chromium, and an organic coating, optionally containing silica, attached to the chromate layer. The coated strip is prepared by depositing a zinc alloy on an extra low carbon steel substrate, subjecting the substrate to a chromate treatment in an aqueous chromate solution containing a chromate compound, a reducing agent, and an acid residue, resin or silica, and applying an organic coating on the chromate layer and baking the coating at a temperature of up to 150 DEG C.

IPC 1-7

B05D 7/14; C23C 28/00

IPC 8 full level

C23C 22/74 (2006.01); **C23C 22/28** (2006.01); **C23C 22/78** (2006.01); **C23C 28/00** (2006.01)

CPC (source: EP KR)

C23C 22/28 (2013.01 - KR); **C23C 22/74** (2013.01 - KR); **C23C 22/78** (2013.01 - EP); **C23C 28/00** (2013.01 - EP)

Cited by

US6107730A; EP1449939A3; EP0308563A1; US5456953A; US2012168317A1; EP0390122A1; US5147729A; DE3836858A1

Designated contracting state (EPC)

BE DE ES FR GB IT SE

DOCDB simple family (publication)

EP 0230320 A1 19870729; EP 0230320 B1 19910130; AU 583444 B2 19890427; AU 6785387 A 19870730; CA 1259532 A 19890919;
DE 3767727 D1 19910307; ES 2020202 B3 19910801; KR 880007795 A 19880829; KR 900006812 B1 19900921

DOCDB simple family (application)

EP 87100847 A 19870122; AU 6785387 A 19870121; CA 528076 A 19870123; DE 3767727 T 19870122; ES 87100847 T 19870122;
KR 870000612 A 19870124