

Title (en)

YTTRIUM ALUMINIUM GARNET PHOSPHOR DEPOSITION TECHNIQUE.

Title (de)

YTTRIUM-ALUMINIUM-GRANAT-PHOSPHOR-ABSETZUNGSTECHNIK.

Title (fr)

TECHNIQUE DE DEPOT D'UNE SURFACE PHOSPHORESCENTE A BASE DE FERRITE GRENADE D'YTTRIUM-ALUMINIUM.

Publication

**EP 0242381 A1 19871028 (EN)**

Application

**EP 86906066 A 19860911**

Priority

US 78684385 A 19851011

Abstract (en)

[origin: WO8702374A1] A phosphor for use in CRTs comprises YAG particles bound to another and to a substrate by a sulphate compound. The phosphor is prepared by treating YAG particles with sulphuric acid, depositing the treated powder on a non-browning glass, quartz or sapphire substrate, and heating to a temperature between about 320°C and 780°C for about 1 h to 2 h in an oxygen ambient.

Abstract (fr)

Substance phosphorescente utilisée dans des tubes à rayons cathodiques et comprenant des particules de ferrite grenat d'yttrium-aluminium liées entre elles et à un substrat par un composé de sulfate. La substance phosphorescente est préparée en traitant les particules de ferrite grenat d'yttrium-aluminium avec de l'acide sulfurique, en déposant la poudre traitée sur un substrat non brunissant en verre, quartz ou saphir, et en chauffant ladite poudre à une température comprise entre 320°C et 780°C environ pendant une à deux heures en présence d'oxygène.

IPC 1-7

**C09K 11/02**

IPC 8 full level

**C09K 11/02** (2006.01); **C09K 11/80** (2006.01); **H01J 29/20** (2006.01)

CPC (source: EP)

**C09K 11/02** (2013.01)

Citation (search report)

See references of WO 8702374A1

Designated contracting state (EPC)

DE FR GB NL SE

DOCDB simple family (publication)

**WO 8702374 A1 19870423**; EP 0242381 A1 19871028; JP S63501083 A 19880421

DOCDB simple family (application)

**US 8601878 W 19860911**; EP 86906066 A 19860911; JP 50529986 A 19860911