

Title (en)
METHOD FOR PICKLING IRON OR STEEL OBJECTS

Publication
EP 0244417 B1 19900509 (EN)

Application
EP 86902076 A 19860317

Priority
SE 8501329 A 19850319

Abstract (en)
[origin: WO8605523A1] A method for pickling iron or steel objects before a subsequent surface treatment or mechanical processing. The objects (11) are transported into a pickling bath (10) having a temperature above 25<o>C and containing a solution of ferrous chloride and a low proportion of free hydrochloric acid. The pickling bath is continuously regenerated in a circulation system with electrolytic cells (14). These are preferably electrically connected in series and in parallel with the flow of the pickling bath, in order to deposit iron on the cathode (19) and recover free acid.

IPC 1-7
C23G 1/08; **C23G 1/36**

IPC 8 full level
C23G 1/08 (2006.01); **C23G 1/36** (2006.01)

CPC (source: EP)
C23G 1/08 (2013.01); **C23G 1/36** (2013.01)

Designated contracting state (EPC)
AT BE DE GB SE

DOCDB simple family (publication)
WO 8605523 A1 19860925; CA 1256357 A 19890627; DE 3671042 D1 19900613; EP 0244417 A1 19871111; EP 0244417 B1 19900509; JP S62502268 A 19870903; SE 452481 B 19871130; SE 8501329 D0 19850319; SE 8501329 L 19860920

DOCDB simple family (application)
SE 8600116 W 19860317; CA 504493 A 19860319; DE 3671042 T 19860317; EP 86902076 A 19860317; JP 50188686 A 19860317; SE 8501329 A 19850319