

Title (en)  
Using a copper alloy.

Title (de)  
Verwendung einer Kupferlegierung.

Title (fr)  
Utilisation d'un alliage cuivreux.

Publication  
**EP 0249740 A2 19871223 (DE)**

Application  
**EP 87106904 A 19870512**

Priority  
DE 3620655 A 19860620

Abstract (en)  
1. Use of a copper alloy comprising 0.2 to 1.2% nickel, 0.04 to 0.25% phosphorus, the remainder copper and impurities resulting from the production process in the hardened state as material for the mould walls of continuous casting moulds.

Abstract (de)  
Verwendung einer Kupferlegierung, bestehend aus 0,2 bis 1,2 % Nickel, 0,04 bis 0,25 % Phosphor, Rest Kupfer und herstellungsbedingte Verunreinigungen im ausgehärteten Zustand als Werkstoff für Stranggiekokillen.

IPC 1-7  
**B22D 11/04; C22C 9/06; C22F 1/057; H01B 1/02**

IPC 8 full level  
**B22D 11/04** (2006.01); **B22D 11/059** (2006.01); **C22C 9/06** (2006.01); **C22F 1/00** (2006.01); **C22F 1/057** (2006.01); **C22F 1/08** (2006.01); **H01B 1/02** (2006.01)

CPC (source: EP KR)  
**B22D 11/059** (2013.01 - EP); **C22C 9/06** (2013.01 - EP KR); **C22F 1/08** (2013.01 - EP)

Cited by  
EP0305986A3; EP1170074A1; FR2751990A1; US6149741A; KR100429109B1

Designated contracting state (EPC)  
AT BE CH DE ES FR GB IT LI SE

DOCDB simple family (publication)  
**EP 0249740 A2 19871223; EP 0249740 A3 19880420; EP 0249740 B1 19891025**; DE 3760850 D1 19891130; ES 2011467 B3 19900116; FI 82893 B 19910131; FI 82893 C 19910510; FI 872327 A0 19870526; FI 872327 A 19871221; JP 2540161 B2 19961002; JP S6324028 A 19880201; KR 88000609 A 19880328; KR 920007884 B1 19920918; MX 170389 B 19930819; ZA 874022 B 19871204

DOCDB simple family (application)  
**EP 87106904 A 19870512**; DE 3760850 T 19870512; ES 87106904 T 19870512; FI 872327 A 19870526; JP 15155187 A 19870619; KR 870006311 A 19870620; MX 696187 A 19870616; ZA 874022 A 19870604