

Title (en)

HEAT TREATMENT OF RAPIDLY QUENCHED FE-6.5 WT SI RIBBON

Publication

EP 0254932 B1 19921021 (EN)

Application

EP 87109970 A 19870710

Priority

US 89413986 A 19860801

Abstract (en)

[origin: EP0254932A2] A rapidly quenched Fe-Si alloy containing 6 to 7 wt% Si is heat treated to promote and control any order-disorder reaction, thereby improving its ac core loss and exciting power at induction levels above B=1.2 T. The alloy has a substantially <100> texture, a grain size of about 1 to 2 mm, a B2 domain size of 100 to 850 nm, a DO3 domain size of about 5 to 25 nm, an ac core loss of about 1.2 to 1.6 W/kg and an exciting power of about 15 to 46 VA/kg, the core loss and exciting power being measured at an induction level of B=1.4 T and a frequency of f=60 Hz.

IPC 1-7

C21D 6/00; H01F 1/16

IPC 8 full level

C21D 1/26 (2006.01); **C21D 6/00** (2006.01); **C21D 8/12** (2006.01); **C22C 38/00** (2006.01); **C22C 38/02** (2006.01); **H01F 1/147** (2006.01); **H01F 1/153** (2006.01)

CPC (source: EP)

C21D 1/26 (2013.01); **C21D 6/008** (2013.01); **H01F 1/14775** (2013.01); **H01F 1/15341** (2013.01)

Cited by

CN112281060A; EP0601549A1

Designated contracting state (EPC)

DE FR GB

DOCDB simple family (publication)

EP 0254932 A2 19880203; EP 0254932 A3 19890719; EP 0254932 B1 19921021; DE 3782288 D1 19921126; DE 3782288 T2 19930304; JP 2684177 B2 19971203; JP S6353242 A 19880307

DOCDB simple family (application)

EP 87109970 A 19870710; DE 3782288 T 19870710; JP 19053387 A 19870731