

Title (en)

PROCESS FOR INCREASING THE ROOM TEMPERATURE DUCTILITY OF AN OXIDE DISPERSION HARDENED NICKEL BASE SUPERALLOY ARTICLE HAVING A COARSE COLUMNAR GRAIN STRUCTURE DIRECTIONALLY ORIENTED ALONG THE LENGTH

Publication

EP 0274631 B1 19910306 (DE)

Application

EP 87117524 A 19871127

Priority

CH 511186 A 19861219

Abstract (en)

[origin: US4795507A] Process for increasing the room-temperature ductility of a workpiece composed of oxide-dispersion-hardened nickel-base superalloy and existing as coarse, longitudinally oriented columnar crystallites by subjecting the previously zone-annealed workpiece to a solution anneal in the temperature range between 1,160 DEG and 1,280 DEG C. under argon atmosphere for 1/2 h to 5 h and then to a purposefully chosen cooling down at a rate of 0.1 DEG C./min to 5 DEG C./min to a temperature of 500 DEG to 700 DEG C. Thereafter the workpiece is cooled down to room temperature in air. Preferred purposefully chosen cooling down rate: approx. 0.5 DEG C./min.

IPC 1-7

C22C 32/00; **C22F 1/10**

IPC 8 full level

C22C 1/10 (2006.01); **C22C 19/05** (2006.01); **C22C 32/00** (2006.01); **C22F 1/00** (2006.01); **C22F 1/10** (2006.01)

CPC (source: EP US)

C22C 1/10 (2013.01 - EP US); **C22C 32/0026** (2013.01 - EP US); **C22F 1/10** (2013.01 - EP US)

Citation (examination)

J.S. Benjamin, Metall. Trans. 1970,1,p. 2943 to 2951; M.Y. Nazmy, R.F. Singer, Scripta Metallurgica, 1985, Vol. 19, p. 829 to 832; T.K. Glasgow, Nasa TM-78973 (1978)

Cited by

EP0398121A1; EP0761826A3; EP0456119A1; EP0442545A1; EP0767252A1; US5725692A; US5788785A; KR100391737B1; EP3421621B1

Designated contracting state (EPC)

CH DE FR GB LI

DOCDB simple family (publication)

EP 0274631 A1 19880720; **EP 0274631 B1 19910306**; CH 671583 A5 19890915; DE 3768464 D1 19910411; JP S63162846 A 19880706; US 4795507 A 19890103

DOCDB simple family (application)

EP 87117524 A 19871127; CH 511186 A 19861219; DE 3768464 T 19871127; JP 31433587 A 19871214; US 13136187 A 19871210