

Title (en)
ACRYLIC FIBRES

Publication
EP 0294135 A3 19890830 (EN)

Application
EP 88304918 A 19880531

Priority
GB 8712811 A 19870601

Abstract (en)
[origin: EP0294135A2] Porous acrylic and modacrylic fibre having a porosity above $0.3\text{ cm}^3\text{g}^{-1}$, an internal surface area of at least $50\text{ m}^2\text{g}^{-1}$ (when its decitex is greater than 2.5) or at least $35\text{ m}^2\text{g}^{-1}$ (when its decitex is not more than 2.5), and a water imbibition of at least 65% (when its decitex is greater than 2.5) or at least 55% (when its decitex is not more than 2.5) and other porous acrylic and modacrylic fibre can be produced by contacting never-dried, standard wet-spun fibre with a water-miscible organic liquid which is a non-solvent for the fibre and has a boiling point below the glass transition temperature of the fibre to exchange the water in the fibre for the organic liquid, and then drying the fibre so as to remove the organic liquid without collapsing the fibre. Porous fibre made in this way or other porous acrylic or modacrylic fibre in dry or never-dried state can be impregnated with an additive either by immersion in a solution of the additive in an organic liquid of the above type or by immersion in a solution or liquid dispersion of the additive in a different liquid followed by exchange of that liquid with an organic liquid of the above type, followed in either case by drying to remove the liquid. The drying conditions can be controlled to provide uncollapsed fibres, fully collapsed fibres or, preferably, novel partially collapsed fibres, from which the additive is released in a sustained fashion at a rate determined by the degree of collapse of the fibres.

IPC 1-7
D01F 6/18; **D01D 5/247**; **D01F 11/06**

IPC 8 full level
D01F 6/18 (2006.01); **D01F 6/38** (2006.01); **D01F 11/06** (2006.01)

CPC (source: EP)
D01F 6/18 (2013.01); **D01F 11/06** (2013.01)

Citation (search report)
• [A] GB 1377200 A 19741211 - MITSUBISHI RAYON CO
• [A] US 3577499 A 19710504 - KNUDSEN JOHN P
• [AD] FR 2342358 A1 19770923 - BAYER AG [DE]
• [A] US 3781391 A 19731225 - SHIMODA K, et al
• [A] GB 1481402 A 19770727 - M & T CHEMICALS INC

Cited by
US5516473A; US9802177B2; WO9509257A1

Designated contracting state (EPC)
BE CH DE ES FR GB IT LI NL SE

DOCDB simple family (publication)
EP 0294135 A2 19881207; **EP 0294135 A3 19890830**; GB 8712811 D0 19870708; JP S63309613 A 19881216

DOCDB simple family (application)
EP 88304918 A 19880531; GB 8712811 A 19870601; JP 13287988 A 19880601