

Title (en)

PROCESS AND APPARATUS FOR MANUFACTURING THIN WIRES, RODS, PIPES OR SECTIONS MADE OF STEELS OR ALLOYS WITH A LOW DEFORMABILITY, PARTICULARLY OF HARDENABLE STEELS

Publication

**EP 0314667 B1 19920408 (DE)**

Application

**EP 88890265 A 19881024**

Priority

AT 284687 A 19871029

Abstract (en)

[origin: EP0314667A1] In the process and equipment for deformation of steels, metals and alloy of low deformability and/or deformation resistance at room temperature from raw material of small thickness, the raw material is heated, preferably by continuous rapid heating, to a temperature of at least 400 DEG C and at most up to the AC1 temperature of the alloy, and a two-stage or multi-stage deformation with an altogether large reduction in cross-section is carried out. <IMAGE>

IPC 1-7

**B21B 1/18**; **B21B 3/02**; **C21D 8/06**; **C21D 9/62**

IPC 8 full level

**B21B 1/16** (2006.01); **B21B 1/18** (2006.01); **B21B 45/00** (2006.01); **C21D 8/06** (2006.01); **C21D 9/62** (2006.01); **B21B 9/00** (2006.01)

CPC (source: EP)

**B21B 1/166** (2013.01); **B21B 1/18** (2013.01); **B21B 45/004** (2013.01); **C21D 8/06** (2013.01); **C21D 9/62** (2013.01); **B21B 9/00** (2013.01)

Cited by

WO9630135A1; AT396073B; EP1607147A1; CN111957756A; DE102004048443B3; US5638714A; EP0442864A1; AT394670B; WO2005123288A1; WO2013028085A1; WO2006050680A1

Designated contracting state (EPC)

AT BE CH DE FR GB IT LI LU NL SE

DOCDB simple family (publication)

**EP 0314667 A1 19890503**; **EP 0314667 B1 19920408**; **EP 0314667 B2 19951213**; AT 393361 B 19911010; AT A284687 A 19910315; AT E74624 T1 19920415; DE 3869902 D1 19920514

DOCDB simple family (application)

**EP 88890265 A 19881024**; AT 284687 A 19871029; AT 88890265 T 19881024; DE 3869902 T 19881024