

Title (en)
PROCESS FOR BLEACHING MECHANICAL WOOD PULP

Publication
EP 0333398 A3 19910807 (EN)

Application
EP 89302431 A 19890313

Priority
GB 8806206 A 19880316

Abstract (en)
[origin: EP0333398A2] A paper pulp refining and bleaching process wherein the pulp is treated in a refiner (10,12) with a sodium hydrosulfite bleach liquor in the presence of a strong alkali such as NaOH, whereby bleaching takes place at alkaline pH, preferably 10 to 12. The process is preferably carried out by passing the pulp successively through a primary refiner (10) at elevated pressure, a secondary refiner (12) at atmospheric pressure and a bleaching tower (14), an alkaline hydrosulfite solution being fed to each.

IPC 1-7
D21B 1/16; **D21C 9/10**

IPC 8 full level
D21B 1/16 (2006.01); **D21C 9/10** (2006.01)

CPC (source: EP US)
D21B 1/16 (2013.01 - EP US); **D21C 9/1084** (2013.01 - EP US)

Cited by
EP0604088A1; US5607547A; EP2071074A1; US8784607B2; WO2008129048A1; US8282773B2

Designated contracting state (EPC)
AT BE CH DE ES FR GR IT LI LU NL SE

DOCDB simple family (publication)
EP 0333398 A2 19890920; **EP 0333398 A3 19910807**; **EP 0333398 B1 19951115**; **EP 0333398 B2 20010411**; AT E130388 T1 19951215; CA 1325868 C 19940111; DE 68924793 D1 19951221; DE 68924793 T2 19960502; DE 68924793 T3 20010705; FI 891248 A0 19890316; FI 891248 A 19890917; FI 96521 B 19960329; GB 2215350 A 19890920; GB 2215350 B 19920520; GB 8806206 D0 19880413; NO 174560 B 19940214; NO 891117 D0 19890315; NO 891117 L 19890918; US 5129987 A 19920714

DOCDB simple family (application)
EP 89302431 A 19890313; AT 89302431 T 19890313; CA 593749 A 19890315; DE 68924793 T 19890313; FI 891248 A 19890316; GB 8806206 A 19880316; NO 891117 A 19890315; US 50657690 A 19900409