

Title (en)

USE OF AN IRON-BASE ALLOY IN THE MANUFACTURE OF SINTERED PARTS WITH A HIGH CORROSION RESISTANCE, A HIGH WEAR RESISTANCE AS WELL AS A HIGH TOUGHNESS AND COMPRESSION STRENGTH, ESPECIALLY FOR USE IN THE PROCESSING OF SYNTHETIC MATERIALS

Publication

**EP 0348380 B1 19921119 (DE)**

Application

**EP 89890163 A 19890614**

Priority

AT 159988 A 19880621

Abstract (en)

[origin: EP0348380A1] Use of an iron-based alloy for the production of sintered parts of high corrosion resistance, high wear resistance, high toughness and high compressive strength, in particular for processing plastics, having a composition, in % by weight, chromium 16.0-29.0, molybdenum 0.4-2.5, tungsten 0.3-2.0, vanadium 3.0-10.0, titanium up to 5.0, aluminium up to 1.0, boron up to 0.05, nitrogen 0.01-0.18, niobium up to 5.0, iron and preparation-related impurities as the remainder, the value formed from  $(\% \text{ of Cr} - 13) + 4.4 \times (\% \text{ of V} - 3) + 2 \times (\% \text{ of Nb}) + 4.2 \times (\% \text{ of Ti})$  being greater than 8.8, and the minimum carbon content of the alloy corresponding to the correlation  $C_{\min} = 0.3 + [(\% \text{ of Cr} - 13) \times 0.06] + [(2 \times \% \text{ of Mo} + W) \times 0.03] + (\% \text{ of V} \times 0.24) + (\% \text{ of Nb} \times 0.13) + (\% \text{ of Ti} \times 0.25)$  and the maximum carbon content of the alloy corresponds to the correlation  $C_{\max} = 0.7 + [(\% \text{ of Cr} - 13) \times 0.06] + [(2 \times \% \text{ of Mo} + W) \times 0.03] + (\% \text{ of V} \times 0.24) + (\% \text{ of Nb} \times 0.13) + (\% \text{ of Ti} \times 0.25)$ , with the proviso that the matrix has a chromium content of at least 13% after hardening and annealing, and the carbide content is at least 25% by volume, the carbide grain size being less than 14  $\mu\text{m}$  and at least 5 % by volume of the carbides being in the form of MC carbides.

IPC 1-7

**C22C 33/02**

IPC 8 full level

**B22F 3/24** (2006.01); **C22C 33/02** (2006.01); **C22C 38/00** (2006.01); **C22C 38/32** (2006.01)

CPC (source: EP)

**C22C 33/0285** (2013.01)

Cited by

EP0721995A3; US5900560A; EP0378925A1; CN111850427A; AT501794A1; AT501794B1; GB2298869A; GB2298869B; CN102905831A; US5936169A; US5679908A; EP3428300A1; US7442338B2; WO2006112912A1; WO03069004A1; WO0073527A1; WO2011115547A1

Designated contracting state (EPC)

AT BE CH DE ES FR GB IT LI LU NL SE

DOCDB simple family (publication)

**EP 0348380 A1 19891227**; **EP 0348380 B1 19921119**; **EP 0348380 B2 19960417**; AT 393642 B 19911125; AT A159988 A 19910515; AT E82595 T1 19921215; AU 3666289 A 19900125; AU 615756 B2 19911010; DE 58902742 D1 19921224; ES 2052971 T3 19940716; ES 2052971 T5 19961001; JP 2583451 B2 19970219; JP H0277556 A 19900316; PT 90925 A 19891229; PT 90925 B 19971031; ZA 894703 B 19920129

DOCDB simple family (application)

**EP 89890163 A 19890614**; AT 159988 A 19880621; AT 89890163 T 19890614; AU 3666289 A 19890620; DE 58902742 T 19890614; ES 89890163 T 19890614; JP 14432389 A 19890608; PT 9092589 A 19890621; ZA 894703 A 19890621