

Title (en)

MAGNESIUM ALLOYS WITH HIGH-MECHANICAL RESISTANCE AND PROCESS FOR OBTAINING THEM BY RAPID SOLIDIFICATION

Publication

EP 0357743 B1 19930929 (FR)

Application

EP 89903172 A 19890223

Priority

- FR 8802885 A 19880226
- FR 8901913 A 19890201

Abstract (en)

[origin: WO8908154A1] Magnesium alloys having a breaking load of at least 290 MPa, in particular at least 330 MPa, having the following composition: Al 2-11 %, Zn 0-12 %, Mn 0-0,6 %, Ca 0-7 %, but with at least the presence of Zn and/or Ca, having an average particle size less than 3 µm, a homogeneous matrix reinforced by intermetallic compounds smaller than 1 µm precipitated at the grain boundaries, this structure remaining unchanged after being maintained for 24h at 200 DEG C; process for producing them by rapid solidification and consolidation by extrusion at a temperature between 200 and 350 DEG C.

IPC 1-7

C22C 23/02

IPC 8 full level

B22D 11/06 (2006.01); **C22C 1/00** (2006.01); **C22C 1/02** (2006.01); **C22C 23/02** (2006.01)

CPC (source: EP US)

C22C 23/02 (2013.01 - EP US); **C22C 23/04** (2013.01 - EP US); **C22C 45/005** (2013.01 - EP US); **C22F 1/06** (2013.01 - EP US)

Designated contracting state (EPC)

DE FR GB

DOCDB simple family (publication)

WO 8908154 A1 19890908; DE 68909544 D1 19931104; DE 68909544 T2 19940127; EP 0357743 A1 19900314; EP 0357743 B1 19930929; FR 2642439 A2 19900803; FR 2642439 B2 19930416; JP H02503331 A 19901011; US 4997622 A 19910305

DOCDB simple family (application)

FR 8900071 W 19890223; DE 68909544 T 19890223; EP 89903172 A 19890223; FR 8901913 A 19890201; JP 50344589 A 19890223; US 42713389 A 19891025