

Title (en)
METHOD FOR MAKING A COMPOSITE YARN

Publication
EP 0364874 B1 19930929 (DE)

Application
EP 89118903 A 19891011

Priority
• DE 3835138 A 19881015
• DE 3841740 A 19881210

Abstract (en)
[origin: EP0364874A2] A composite yarn is produced by combining a low-stretch and a high-stretch yarn. The high-stretch yarn can be in, for example, polyurethane. The low-stretch yarn can be a thermoplastic yarn. It is known to be difficult to produce a sufficiently compact combination of such yarns by an air jet treatment at high speeds. <??>As a remedy, the low-stretch yarn is subjected to a spreading treatment immediately before being combined with the elastane yarn. The spreading treatment can be effected mechanically, for example by false twisting and detwisting the false twist, by drawing over an edge or by treatment in a spreading nozzle. <IMAGE>

IPC 1-7
D02G 3/32; D02J 1/08

IPC 8 full level
D02G 3/32 (2006.01); **D02J 1/08** (2006.01)

CPC (source: EP US)
D02G 1/0266 (2013.01 - EP US); **D02G 1/20** (2013.01 - EP US); **D02G 3/328** (2013.01 - EP US); **D02J 1/08** (2013.01 - EP US)

Cited by
FR2749859A1; DE19746878B4; US6840032B2; WO2007054334A1; WO9748843A1

Designated contracting state (EPC)
CH DE FR GB IT LI

DOCDB simple family (publication)
EP 0364874 A2 19900425; EP 0364874 A3 19901212; EP 0364874 B1 19930929; DE 58905762 D1 19931104; US 5008992 A 19910423

DOCDB simple family (application)
EP 89118903 A 19891011; DE 58905762 T 19891011; US 42057189 A 19891012