

Title (en)
Soft ocular lens material.

Title (de)
Weiches Material für Okularlinsen.

Title (fr)
Matériel pour lentille oculaire souple.

Publication
EP 0379146 B1 19950517 (EN)

Application
EP 90100840 A 19900116

Priority
• JP 884589 A 19890117
• JP 3521889 A 19890215
• JP 17850089 A 19890711

Abstract (en)
[origin: EP0379146A2] A soft ocular lens material made of a copolymer consisting essentially of: (A) from 5 to 70 parts by weight of a fluorine-containing (meth)acrylate; (B) from 5 to 60 parts by weight of an alkyl (meth)acrylate; (C) from 3 to 45 parts by weight of a polysiloxane macromonomer having polymerizable groups at both terminals, of the formula I: <CHEM> wherein each of Y<1><1> and Y<1><2> independently represents an acryloyl group, a methacryloyl group, a vinyl group or an allyl group; each of X<1><1> and X<1><2> independently represents a covalent bond, an oxygen atom or an alkylene glycol group; each of R<1><1> and R<1><2> independently represents a linear or branched alkylene group having from 1 to 6 carbon atoms; each of R<1><3>, R<1><4>, R<1><5>, R<1><6>, R<1><7> and R<1><8> independently represents an alkyl group having from 1 to 3 carbon atoms or a phenyl group; i is an integer of from 1 to 1500; and j is an integer of from 0 to 1499 (provided that i+j is at most 1500); and (D) from 3 to 40 parts by weight of a polysiloxane macromonomer having polymerizable groups bonded via one or two urethane bonds to the siloxane main chain, of the formula II: <CHEM> wherein each of Y<2><1> and Y<2><2> independently represents a group selected from the group consisting of an acryloyloxy group, a methacryloyloxy group, a vinyl group and an allyl group; each of R<3><1> and R<3><4> independently represents a linear or branched alkylene group having from 2 to 6 carbon atoms; each of X<2><1> and X<2><2> independently represents a covalent bond, an oxygen atom or an alkylene glycol group; each of R<3><2> and R<3><3> independently represents a linear or branched alkylene group having from 1 to 6 carbon atoms; each of R<2><3>, R<2><4>, R<2><5>, R<2><6>, R<2><7> and R<2><8> independently represents an alkyl group having from 1 to 3 carbon atoms or a phenyl group; each of E<2><1> and E<2><2> independently represents -NHCO- (provided that in this case, each of X<2><1> and X<2><2> is a covalent bond, E<2><1> forms a urethane bond together with X<2><5>, and E<2><2> forms a urethane bond together with X<2><6>) or a bivalent group derived from a diisocyanate selected from the group consisting of saturated aliphatic, alicyclic and aromatic diisocyanates (provided that in this case, each of X<2><1> and X<2><2> independently represents an oxygen atom or an alkylene glycol group, E<2><1> forms a urethane bond together With X<2><1> and X<2><5>, and E<2><2> forms a urethane bond together with X<2><2> and X<2><6>); each of X<2><5> and X<2><6> independently represents an oxygen atom, an alkylene glycol or a group represented by the formula V: <CHEM> wherein R<4><1> is a trivalent hydrocarbon group having from 1 to 6 carbon atoms; Y<2><3> represents a group selected from the group consisting of an acryloyloxy group, a methacryloyloxy group, a vinyl group and an allyl group; R<3><6> represents a linear or branched alkylene group having from 2 to 6 carbon atoms; X<2><3> represents a covalent bond, an oxygen atom or an alkylene glycol group; E<2><3> represents -NHCO- (provided that in this case, X<2><3> is a covalent bond) or a bivalent group derived from a diisocyanate selected from the group consisting of saturated aliphatic, alicyclic and aromatic diisocyanates (provided that in this case, X<2><3> is an oxygen atom or an alkylene glycol group), which forms a urethane bond together with X<2><3> and the adjacent oxygen atom bonded to R<4><1>; a is an integer of from 1 to 1500; and b is an integer of from 0 to 1499, provided a+b <= 1500; as essential copolymer components. <

IPC 1-7
C08F 220/22; **C08F 220/12**; **C08F 230/08**; **G02B 1/04**; **C08F 283/12**

IPC 8 full level
C08F 220/22 (2006.01); **C08F 230/08** (2006.01); **C08F 283/12** (2006.01); **C08F 290/06** (2006.01); **C08F 290/14** (2006.01); **G02B 1/04** (2006.01)

CPC (source: EP US)
C08F 220/22 (2013.01 - EP US); **C08F 283/124** (2013.01 - EP US); **C08F 290/068** (2013.01 - EP US); **C08F 290/148** (2013.01 - EP US); **G02B 1/043** (2013.01 - EP US)

Cited by
EP0648243A4; EP0898972A3; US5416180A; EP0600269A3; EP0461604A3; US5269813A; EP0381005A3; US5603774A; EP0657751A3; US5882421A; CN100403059C; CN1048021C; US9248614B2; US9921340B2; US6326448B1; WO2006002894A1; WO9911683A1; WO0034347A1

Designated contracting state (EPC)
DE FR GB

DOCDB simple family (publication)
EP 0379146 A2 19900725; **EP 0379146 A3 19910828**; **EP 0379146 B1 19950517**; AU 4779890 A 19900726; AU 615369 B2 19910926; CA 2007852 A1 19900717; CA 2007852 C 20000523; DE 69019382 D1 19950622; DE 69019382 T2 19960328; US 4954586 A 19900904

DOCDB simple family (application)
EP 90100840 A 19900116; AU 4779890 A 19900109; CA 2007852 A 19900116; DE 69019382 T 19900116; US 46066290 A 19900103