

Title (en)

Process for preparation of grain-oriented electrical steel sheet having superior magnetic properties

Title (de)

Verfahren zum Herstellen kornorientierter Elektrobleche mit verbesserten magnetischen Eigenschaften

Title (fr)

Procédé pour produire de tôle d'acier électrique à grain orienté possédant des caractéristiques magnétiques améliorées

Publication

EP 0392535 B2 20021016 (EN)

Application

EP 90107030 A 19900412

Priority

- JP 9441289 A 19890414
- JP 9441389 A 19890414

Abstract (en)

[origin: EP0392535A2] A silicon steel slab comprising 0.05 to 0.8% by weight of Mn and up to 0.014% by weight of S + 0.405Se is heated at a temperature lower than 1280 DEG C and hot-rolled under such conditions that the hot rolling-finish temperature is 700 to 1150 DEG C, the cumulative reduction ratio at the final three passes is at least 40%, and the reduction ratio at the final pass is at least 20%, or this silicon steel slab is hot-rolled at a hot rolling-finish temperature of 750 to 1150 DEG C while adopting the above-mentioned reduction ratio according to need, is maintained at a temperature not lower than 700 DEG C for at least 1 second, and wound at a winding temperature lower than 700 DEG C. The hot-rolled sheet is subjected to the hot-rolled sheet annealing, finally cold-rolled at a reduction ratio of at least 80%, subjected to the decarburization annealing, and then subjected to the final finish annealing. According to this process, a grain-oriented electrical steel sheet having superior magnetic properties is obtained.

IPC 1-7

C21D 8/12

IPC 8 full level

C21D 8/12 (2006.01)

CPC (source: EP)

C21D 8/1222 (2013.01); **C21D 8/1233** (2013.01)

Cited by

WO2008000396A1; WO9848062A1

Designated contracting state (EPC)

DE FR GB IT SE

DOCDB simple family (publication)

EP 0392535 A2 19901017; **EP 0392535 A3 19920930**; **EP 0392535 B1 19950927**; **EP 0392535 B2 20021016**; DE 69022617 D1 19951102; DE 69022617 T2 19960321; DE 69022617 T3 20030403

DOCDB simple family (application)

EP 90107030 A 19900412; DE 69022617 T 19900412