

Title (en)

Thermosetting resin composition and thermosetting dry film.

Title (de)

Warmhärtende Harzzusammensetzung und warmhärtender trockener Film.

Title (fr)

Composition de résine thermodurcissable et film sec thermodurcissable.

Publication

**EP 0393638 A2 19901024 (EN)**

Application

**EP 90107371 A 19900418**

Priority

JP 9625189 A 19890418

Abstract (en)

A thermosetting resin composition, a solution composition of the resin and a thermosetting dry film formed out of the resin are disclosed. The thermosetting resin composition contains a specific resin component as the main component. The resin component consists of (A) 100 weight parts of an aromatic polyimide; and (B) 5 to 2,000 weight parts of (a) a terminal-modified imide oligomer or (b) an unsaturated imide compound. The aromatic polyimide (A) is formed from a tetracarboxylic acid ingredient which contains 2,3,3' min ,4 min -biphenyltetracarboxylic acid or its derivative in an amount of at least 60 mole % and an aromatic diamine ingredient. The polyimide has such a high molecular weight that the logarithmic viscosity (concentration: 0.5 g/100 ml of solvent; solvent: N-methyl-2-pyrrolidone; and temperature of measurement: 30 DEG C) is not less than 0.2. The polyimide is soluble in an organic polar solvent. The imide oligomer (a) has an internal imide bond inside of the oligomer and an unsaturated group as a terminal group, and is formed by a reaction of an aromatic tetracarboxylic acid ingredient, a diamine ingredient, and an unsaturated monoamine or dicarboxylic acid ingredient having an unsaturated group. The oligomer has a logarithmic viscosity of not more than 0.5 and a softening point of not higher than 300 DEG C. The imide compound (b) has an internal imide bond inside of the compound and an unsaturated group as a terminal group, and is formed by a reaction of an aromatic tetracarboxylic acid ingredient with a monoamine ingredient having an unsaturated group. The compound has a softening point of not higher than 300 DEG C.

IPC 1-7

**C08L 79/08**; **C09D 179/08**

IPC 8 full level

**C08J 5/18** (2006.01); **C08G 73/10** (2006.01); **C08L 79/08** (2006.01); **C09D 179/08** (2006.01); **H05K 1/03** (2006.01); **H05K 3/38** (2006.01)

CPC (source: EP US)

**C08L 79/08** (2013.01 - EP US); **C08L 79/085** (2013.01 - EP US); **C09D 179/08** (2013.01 - EP US); **H05K 1/0346** (2013.01 - EP US); **H05K 3/386** (2013.01 - EP US); **Y10T 428/31721** (2015.04 - EP US)

Cited by

GB2256643A; US5241018A

Designated contracting state (EPC)

DE FR GB

DOCDB simple family (publication)

**EP 0393638 A2 19901024**; **EP 0393638 A3 19911218**; **EP 0393638 B1 19950111**; DE 69015860 D1 19950223; DE 69015860 T2 19950622; JP 2597181 B2 19970402; JP H02274762 A 19901108; US 5128444 A 19920707

DOCDB simple family (application)

**EP 90107371 A 19900418**; DE 69015860 T 19900418; JP 9625189 A 19890418; US 51001690 A 19900417