

Title (en)  
METHOD FOR MAKING DISPERSED METAL POWDERS

Publication  
**EP 0397877 A4 19910508 (DE)**

Application  
**EP 89902701 A 19881125**

Priority  
SU 8800242 W 19881125

Abstract (en)  
[origin: WO9006200A1] A method for making dispersed metal powders includes treating solid hydrates of metal mineral salts with alkaline solutions of a concentration equal to 6-15 mol/l at a 1.5 to 2-fold excess of alkali contained in that solution in relation to its quantity stoichiometrically required for obtaining the hydroxide. The obtained metal hydroxides are filtered, dried and reduced by hydrogen. The reduction is effected at a temperature 200 to 300C higher than that at the start of reduction of hydroxides of the corresponding metals at a hydrogen consumption of 2.5 to 6m<sup>3</sup>/mol Mexh on the basis of the initial salt. After reduction, the obtained powders are passivated with an inert gas.

IPC 1-7  
**B22F 9/22**

IPC 8 full level  
**B22F 9/18** (2006.01); **B22F 9/22** (2006.01)

CPC (source: EP)  
**B22F 9/22** (2013.01)

Citation (search report)

- [E] US 4798623 A 19890117 - CHERESNOWSKY MICHAEL J [US]
- [A] EP 0080996 A2 19830608 - VOEST ALPINE AG [AT]
- [A] GB 2023112 A 19791228 - GTE SYLVANIA INC
- [A] US 4214896 A 19800729 - CHERESNOWSKY MICHAEL J [US]
- [A] US 4414021 A 19831108 - WELBON WILLIAM W [US]
- [A] US 3833351 A 19740903 - NESKORA D, et al
- [A] US 3877931 A 19750415 - NESKORA DANIEL R, et al
- [A] PATENT ABSTRACTS OF JAPAN, Band 11, Nr. 364 (M-646), 27. November 1987; & JP-A-62 139 803 (OKAMURA SEIYU K.K.) 23-06-1987
- See references of WO 9006200A1

Designated contracting state (EPC)  
CH DE FR GB LI SE

DOCDB simple family (publication)  
**WO 9006200 A1 19900614**; DD 284826 A5 19901128; EP 0397877 A1 19901122; EP 0397877 A4 19910508; FI 903712 A0 19900724; JP H03502345 A 19910530

DOCDB simple family (application)  
**SU 8800242 W 19881125**; DD 32922589 A 19890602; EP 89902701 A 19881125; FI 903712 A 19900724; JP 50262189 A 19881125