

Title (en)

PROCESS FOR MAKING SPLIT LEATHER AND ITS APPLICATION

Publication

EP 0432300 B1 19930609 (DE)

Application

EP 89123040 A 19891213

Priority

EP 89123040 A 19891213

Abstract (en)

[origin: EP0432300A1] To make split leather, a limed animal hide is split into a grain split and a flesh split, the flesh split is divided into a butt and a neck and flank part and the butt is relimed, bated, chrome-tanned, fat-liquored, dried and dressed. Here low-shrinkage split leather is obtained by first reducing the butt, between the chrome-tanning and the fat liquoring, to a thickness of 1.1 to 2.5 mm by shaving on the split and flesh side, retanning, and, after the dried butt has been dressed on the split side, producing from it a middle split 0.5 to 1.0 mm in thickness by shaving on the flesh side, and subsequently dressing the middle split also on the flesh side. This low-shrinkage split leather is particularly suitable for two-dimensionally adhered leather trim subjected to temperature and humidity changes, in particular in motor cars.

IPC 1-7

C14B 1/00

IPC 8 full level

B05D 7/24 (2006.01); **C14B 1/00** (2006.01); **C14B 1/02** (2006.01); **C14B 13/00** (2006.01); **C14C 3/06** (2006.01); **C14C 9/02** (2006.01); **C14C 11/00** (2006.01)

CPC (source: EP US)

C14B 1/00 (2013.01 - EP US)

Cited by

WO2008037945A1; WO2014118037A1; EP2762575B1

Designated contracting state (EPC)

AT BE DE ES FR GB IT NL SE

DOCDB simple family (publication)

EP 0432300 A1 19910619; EP 0432300 B1 19930609; AT E90395 T1 19930615; DE 58904659 D1 19930715; JP H05255700 A 19931005; US 5269814 A 19931214; ZA 909643 B 19910925

DOCDB simple family (application)

EP 89123040 A 19891213; AT 89123040 T 19891213; DE 58904659 T 19891213; JP 40991190 A 19901212; US 62422190 A 19901204; ZA 909643 A 19901130