

Title (en)
CERAMIC PORT LINERS

Publication
EP 0437302 A3 19910807 (EN)

Application
EP 91200811 A 19880323

Priority

- EP 88302531 A 19880323
- JP 6376587 U 19870427
- JP 6376687 U 19870427
- JP 6376787 U 19870427
- JP 7011387 A 19870324
- JP 10405587 A 19870427

Abstract (en)
[origin: EP0285312A2] Ceramic materials to be insert-cast contain not less than 65% of aluminum titanate as a crystalline phase, and have an average particle diameter of crystals thereof being not less than 10 μ m, Young's modulus of 50 to 2,000 kgf/mm², compression strength of 5 to 40 kgf/mm², and porosity of 5 to 35%. These liners are free from cracking due to compression force during insert-casting, peeling-off during use, and facilitate insert-casting. In a port liner having a depressed portion at an outer peripheral surface, a reinforcement is filled into the depression which meets either one or both of requirements that differences in coefficient of thermal expansion at 800 DEG C and Young's modulus between the reinforcement and the material of the liner body are in a range of $\pm 0.1\%$ and in a range of $\pm 1,000$ kgf/mm², respectively. Alternatively, the outer peripheral surface of the port liner body is worked to give an uneven surface where the liner is joined to a metal in insert-casting, or a stress-releasing slit may be formed in a wall of the port liner body. Further, the outer peripheral surface of the ceramic port liner body may be covered with a ceramic sheet which is irreversibly expandable by heating.

IPC 1-7
F02F 1/42; **F02B 77/02**; **F02F 7/00**

IPC 8 full level
C04B 35/46 (2006.01); **C04B 35/478** (2006.01); **F01N 13/10** (2010.01); **F01N 13/16** (2010.01); **F02B 77/02** (2006.01); **F02F 1/42** (2006.01); **F02F 7/00** (2006.01); **F02B 1/02** (2006.01); **F02B 1/04** (2006.01); **F02B 3/06** (2006.01); **F02F 1/24** (2006.01)

CPC (source: EP US)
C04B 35/46 (2013.01 - EP US); **C04B 35/478** (2013.01 - EP US); **F01N 13/102** (2013.01 - EP US); **F01N 13/16** (2013.01 - EP US); **F02B 77/02** (2013.01 - EP US); **F02F 1/4214** (2013.01 - EP US); **F02F 1/4271** (2013.01 - EP US); **F02F 7/0087** (2013.01 - EP US); **F02B 1/02** (2013.01 - EP US); **F02B 1/04** (2013.01 - EP US); **F02B 3/06** (2013.01 - EP US); **F02F 1/4264** (2013.01 - EP US); **F02F 2001/008** (2013.01 - EP US); **F02F 2001/245** (2013.01 - EP US); **F02F 2001/4278** (2013.01 - EP US); **F02F 2200/06** (2013.01 - EP US); **F05C 2203/08** (2013.01 - EP US); **F05C 2251/042** (2013.01 - EP US); **F05C 2253/16** (2013.01 - EP US)

Citation (search report)

- [E] EP 0279904 A2 19880831 - FELDMUEHLE AG [DE]
- [Y] EP 0107268 A2 19840502 - NGK INSULATORS LTD [JP]
- [Y] EP 0146731 A2 19850703 - PORSCHE AG [DE]
- [A] EP 0141540 A2 19850515 - MAZDA MOTOR [JP], et al
- [A] PATENT ABSTRACTS OF JAPAN vol. 8, no. 35 (M-276)(1472) 15 February 1984, & JP-A-58 190537 (HINO JIDOSHA KOGYO K.K) 7 November 1983,
- [A] PATENT ABSTRACTS OF JAPAN vol. 8, no. 5 (M-267)(1442) 11 January 1984, & JP-A-58 167848 (TOYOTA JIDOSHA KOGYO K.K) 4 October 1983,

Cited by
GB2231921B; GB2269633A; GB2269633B

Designated contracting state (EPC)
DE FR GB IT SE

DOCDB simple family (publication)
EP 0285312 A2 19881005; **EP 0285312 A3 19890322**; **EP 0285312 B1 19941221**; DE 3851638 D1 19941027; DE 3851638 T2 19950323; DE 3852513 D1 19950202; DE 3852513 T2 19950713; DE 3853299 D1 19950413; DE 3853299 T2 19950914; EP 0437302 A2 19910717; EP 0437302 A3 19910807; EP 0437302 B1 19940921; EP 0437303 A2 19910717; EP 0437303 A3 19910731; EP 0437303 B1 19950308; US 5055435 A 19911008

DOCDB simple family (application)
EP 88302531 A 19880323; DE 3851638 T 19880323; DE 3852513 T 19880323; DE 3853299 T 19880323; EP 91200811 A 19880323; EP 91200812 A 19880323; US 50853290 A 19900412