

Title (en)
High strength polyester yarn and method for its production

Title (de)
Hochfestes Polyestergarn und Verfahren zu seiner Herstellung

Title (fr)
Fil polyester à haute résistance et procédé pour sa fabrication

Publication
EP 0526740 B1 19980325 (DE)

Application
EP 92111195 A 19920702

Priority
DE 4122324 A 19910705

Abstract (en)
[origin: EP0526740A2] A polyester yarn having a novel property combination of high strength, high modulus and low heat shrinkage is described, which is to be produced by high-speed spinning, and a spinning yarn suitable for its production composed of a polyester raw material based on a modified polyethylene terephthalate which contains as modification components, relative to the total acid components, 0.5 - 5.0 mol % of radicals of aliphatic dicarboxylic acids having in total at least 5 C atoms and/or aromatic dicarboxylic acids whose carbonyl bonds are angled or whose aromatic rings carry modification-active substituents, and/or, relative to the total diol components, contains 0.5 to 5 mol % of alkane or cycloalkane diols having 3 to 10 C atoms, di- or tri-ethylene glycol or polyethylene glycol having a molecular weight of up to 4000, has a specific viscosity, measured in a solution of 1 g of the polyester in 100 ml of dichloroacetic acid at 25 DEG C of 0.8 - 1.7, and in that, when it is spun at a spinning take-off rate V_a , the quotient Q of double refraction and crystallinity corresponds to the formula $11.86 - 3.94 \cdot 10^{-3} \cdot \text{DOLLAR } V_a + 4.57 \cdot 10^{-7} \cdot \text{DOLLAR } (V_a)^2 > Q > 10.86 - 3.94 \cdot 10^{-3} \cdot \text{DOLLAR } V_a + 4.57 \cdot 10^{-7} \cdot \text{DOLLAR } (V_a)^2 > (III)$ <IMAGE>

IPC 1-7
D01F 6/84

IPC 8 full level
C08G 63/91 (2006.01); **D01F 6/62** (2006.01); **D01F 6/84** (2006.01); **D01F 6/86** (2006.01)

CPC (source: EP)
D01F 6/84 (2013.01)

Cited by
US5658662A; DE10201834A1; DE10201834B4; EP0661393A1; WO2005019301A1; WO2011057708A1

Designated contracting state (EPC)
DE FR LU NL

DOCDB simple family (publication)
EP 0526740 A2 19930210; **EP 0526740 A3 19930630**; **EP 0526740 B1 19980325**; BR 9202595 A 19930316; DE 59209248 D1 19980430; IE 922193 A1 19930113; JP H05279919 A 19931026; MX 9203952 A 19930101

DOCDB simple family (application)
EP 92111195 A 19920702; BR 9202595 A 19920703; DE 59209248 T 19920702; IE 922193 A 19920703; JP 17818792 A 19920706; MX 9203952 A 19920703