

Title (en)

ETHYLENE VINYL SILANE COPOLYMER AND ITS PREPARATION.

Title (de)

ETHYLEN-VINYLSILAN COPOLYMER UND SEINE HERSTELLUNG.

Title (fr)

COPOLYMERE D'ETHYLENE/SILANE DE VINYLE ET PREPARATION DE CE COMPOSE.

Publication

EP 0528806 A1 19930303 (EN)

Application

EP 91906600 A 19910405

Priority

FI 902479 A 19900518

Abstract (en)

[origin: WO9118032A1] For improving the mixability of two usually nonmixable polymers and for preventing a complete phase separation during handling, one polymer can be grafted on the other. In this invention is etherified an ethylene vinyl silane polymer containing methoxy groups with another polymer containing hydroxy groups or with a monomer containing hydroxy groups. For example by blending the copolymer of styrene and hydroxy ethyl methacrylate with the terpolymer of ethyl butyl acrylate and vinyl trimethoxy silane, the copolymer is grafted with the silane terpolymer via etherification of the hydroxy groups and the methoxy groups. Alternatively, styrene and hydroxy ethyl methacrylate can be blended with a silane terpolymer by first etherifying the hydroxy groups of the methacrylate monomer and the methoxy groups of the terpolymer and by then copolymerizing styrene with hydroxy ethyl methacrylate. The resulting product is very homogenous and it can be used as compatibilizer and an adhesion plastic and as a polymer component in rubber bitumens.

Abstract (fr)

Pour améliorer la miscibilité de deux polymères habituellement non miscibles et pour empêcher une séparation de phase complète pendant leur manipulation, l'un des deux polymères peut être greffé sur l'autre. A cet effet, on étherifie un polymère d'éthylène/silane de vinyle contenant des groupes méthoxy avec un autre polymère contenant des groupes hydroxy ou avec un monomère contenant des groupes hydroxy. Par exemple, en mélangeant le copolymère de méthacrylate d'hydroxyéthyle et de styrène avec le terpolymère d'acrylate d'éthyle et butyle et de silane triméthoxy de vinyle, on amène le copolymère à se greffer avec le terpolymère de silane par étherification des groupes hydroxy et des groupes méthoxy. Dans une variante, le méthacrylate d'hydroxyéthyle et de styrène peut être mélangé avec un terpolymère de silane, d'abord par étherification des groupes hydroxy du monomère de méthacrylate et des groupes méthoxy du terpolymère, puis par copolymérisation du styrène avec du méthacrylate d'hydroxyéthyle. Le produit qui en résulte est très homogène et peut être utilisé comme agent de compatibilité, comme plastique adhésif et comme composant polymère dans des bitumes à base de caoutchouc.

IPC 1-7

C08F 255/00; **C08F 291/06**

IPC 8 full level

C08F 290/00 (2006.01); **C08F 290/12** (2006.01); **C08F 299/00** (2006.01)

CPC (source: EP)

C08F 290/12 (2013.01); **C08F 299/00** (2013.01)

Citation (search report)

See references of WO 9118032A1

Designated contracting state (EPC)

AT BE CH DE DK ES FR GB GR IT LI LU NL SE

DOCDB simple family (publication)

WO 9118032 A1 19911128; EP 0528806 A1 19930303; FI 902479 A0 19900518; FI 902479 A 19911119; JP H05507098 A 19931014

DOCDB simple family (application)

FI 9100099 W 19910405; EP 91906600 A 19910405; FI 902479 A 19900518; JP 50690491 A 19910405