

Title (en)

PROPYLENE POLYMER COMPOSITION

Publication

EP 0583132 A3 19940713 (EN)

Application

EP 93306136 A 19930803

Priority

JP 20913292 A 19920805

Abstract (en)

[origin: EP0583132A2] A propylene polymer composition comprises [A] 55-85% by weight of a propylene block copolymer containing 2-15 mol% ethylene units, having 5-15 mol% of a portion soluble in n-decane at ordinary temperature and a melt flow rate of 15-60 g/10 min, [B] 5-15% by weight of an ethylene-propylene copolymer rubber containing 70-90 mol% ethylene units having a melt flow rate of 0.1-2.0 g/10 min, [C] 5-15% by weight of an ethylene-propylene-diene copolymer rubber containing 70-90 mol% ethylene units , 8-13 mol% diene units, and having a melt flow rate of 0.1-0.4 g/10 min. [D] 8-20% by weight of an ethylene-butene-1 copolymer rubber containing 85-95 mol% ethylene units and having a melt flow rate of 1.0-10.0 g/10 min, and [E] 5-15% by weight of talc. 55

IPC 1-7

C08L 53/00; C08L 23/16; C08K 3/34

IPC 8 full level

C08K 3/34 (2006.01); **C08L 53/00** (2006.01)

CPC (source: EP US)

C08K 3/34 (2013.01 - EP US); **C08L 53/00** (2013.01 - EP US)

Citation (search report)

- [X] EP 0069479 A1 19830112 - TOA NENRYO KOGYO KK [JP]
- [Y] EP 0265075 A2 19880427 - MITSUI TOATSU CHEMICALS [JP], et al
- [Y] GB 2206886 A 19890118 - MITSUI PETROCHEMICAL IND, et al
- [A] GB 2246358 A 19920129 - NISSAN MOTOR [JP], et al
- [A] EP 0132968 A2 19850213 - MITSUI PETROCHEMICAL IND [JP]

Cited by

EP0754727A1; US5883174A; EP3786229A4

Designated contracting state (EPC)

DE FR GB IT NL

DOCDB simple family (publication)

EP 0583132 A2 19940216; EP 0583132 A3 19940713; EP 0583132 B1 19961127; DE 69306194 D1 19970109; DE 69306194 T2 19970424;
US 5567759 A 19961022

DOCDB simple family (application)

EP 93306136 A 19930803; DE 69306194 T 19930803; US 42762395 A 19950421