

Title (en)
COMPOSITION AND PROCESS FOR TREATING TINPLATE

Title (de)
ZUSAMMENSETZUNG UND VERFAHREN ZUM BEHANDELN VON VERZINNTEN STAHLPLATTEN

Title (fr)
COMPOSITION ET PROCEDE DE TRAITEMENT D'UNE FEUILLE DE TOLE EN FER-BLANC

Publication
EP 0673445 B1 19990519 (EN)

Application
EP 94902385 A 19931201

Priority
• JP 35151892 A 19921209
• US 9311435 W 19931201

Abstract (en)
[origin: WO9413855A1] To impart an excellent corrosion resistance and adherence to the surface of tinplate while avoiding the production of sludge in the treatment bath during continuous treatment, a bath is used that contains phosphate ions, from 0.1 to 5.0 g/L of chelating agent, and tin ions; has a pH from 2.0 to 4.5; is essentially free of oxidizing agent and ferric ion; and has an oxidation-reduction potential of ≤ 450 mV more oxidizing than a silver-saturated silver chloride reference electrode.

IPC 1-7
C23C 22/08; **C23C 22/23**

IPC 8 full level
C23C 22/07 (2006.01); **C23C 22/08** (2006.01); **C23C 22/23** (2006.01); **C23C 22/47** (2006.01)

CPC (source: EP)
C23C 22/08 (2013.01); **C23C 22/23** (2013.01); **C23C 22/47** (2013.01)

Designated contracting state (EPC)
BE DE ES FR GB IT NL

DOCDB simple family (publication)
WO 9413855 A1 19940623; AU 5677594 A 19940704; DE 69325035 D1 19990624; DE 69325035 T2 20000127; EP 0673445 A1 19950927; EP 0673445 A4 19970502; EP 0673445 B1 19990519; JP 3256009 B2 20020212; JP H06173024 A 19940621; ZA 939171 B 19940808

DOCDB simple family (application)
US 9311435 W 19931201; AU 5677594 A 19931201; DE 69325035 T 19931201; EP 94902385 A 19931201; JP 35151892 A 19921209; ZA 939171 A 19931207