

Title (en)

NON-HEAT-TREATED HOT-FORGING STEEL EXCELLENT IN TENSILE STRENGTH, FATIGUE STRENGTH AND MACHINABILITY.

Title (de)

WÄRMEUNBEHANDELTEN WARMGESCHMIEDETER STAHL MIT HERVORRAGENDER ZUGFESTIGKEIT, ERMÜDUNGSFESTIGKEIT UND BEARBEITBARKEIT.

Title (fr)

ACIER DE FORGEAGE A CHAUD SANS TRAITEMENT THERMIQUE, PRESENTANT D'EXCELLENTE CARACTERISTIQUES DE RESISTANCE A LA TRACTION ET A LA FATIGUE ET UNE TRES BONNE APTITUDE A L'USINAGE.

Publication

EP 0674014 A1 19950927 (EN)

Application

EP 94929026 A 19941011

Priority

- JP 9401693 W 19941011
- JP 25433593 A 19931012

Abstract (en)

A non-heat-treated ferritic-bainitic steel to be used as hot-forged, wherein the following relation holds between the bainitic structure fraction f and the carbon content $C(\%)$: $1.4C + 0.4 \geq f \geq 1.4C$ in the metal structure after hot forging a steel material containing the following elements on the weight basis: C: 0.10 SIMILAR 0.35 %; Si: 0.15 SIMILAR 2.00 %; Mn: 0.40 SIMILAR 2.00 %; S: 0.03 SIMILAR 0.10 %; Al: 0.0005 SIMILAR 0.05 %; Ti: 0.003 SIMILAR 0.05 %; N: 0.0020 SIMILAR 0.0070 %; V: 0.30 SIMILAR 0.70 % and further containing at least one of Cr, Mo, Nb, Pb and Ca in a specified amount and cooling the forged steel to room temperature. It is possible to produce a non-heat-treated hot-forging steel having high tensile strength, fatigue strength and machinability.

IPC 1-7

C22C 38/14; **C22C 38/28**; **C22C 38/60**

IPC 8 full level

C22C 38/00 (2006.01); **C22C 38/14** (2006.01); **C22C 38/28** (2006.01); **C22C 38/60** (2006.01)

CPC (source: EP KR)

C22C 38/001 (2013.01 - EP); **C22C 38/14** (2013.01 - KR); **C22C 38/28** (2013.01 - EP KR); **C22C 38/60** (2013.01 - EP KR)

Cited by

CN105734414A; EP1676932A1; EP1201774A3; FR2774098A1; WO9939018A1

Designated contracting state (EPC)

DE FR GB IT

DOCDB simple family (publication)

WO 9510637 A1 19950420; CN 1039035 C 19980708; CN 1115582 A 19960124; DE 69419720 D1 19990902; DE 69419720 T2 19991216; EP 0674014 A1 19950927; EP 0674014 A4 19960207; EP 0674014 B1 19990728; JP 3241897 B2 20011225; JP H07109545 A 19950425; KR 0180938 B1 19990218; KR 950704530 A 19951120

DOCDB simple family (application)

JP 9401693 W 19941011; CN 94190781 A 19941011; DE 69419720 T 19941011; EP 94929026 A 19941011; JP 25433593 A 19931012; KR 19950702391 A 19950612