

Title (en)

Process for dyeing aminated polyester/cotton mix fabric, with disperse reactive dyestuff

Title (de)

Verfahren zum Färben aminierter Cellulose-/Polyester-Mischgewebe mit faserreaktiven Dispersionsfarbstoffen

Title (fr)

Procédé pour teindre des tissus en mélanges cellulose aminée polyester avec des colorants dispersés réactifs

Publication

EP 0690166 A3 19960501 (DE)

Application

EP 95109421 A 19950619

Priority

DE 4422707 A 19940629

Abstract (en)

[origin: EP0690166A2] A process for dyeing cellulose or cellulose/polyester fibre materials (I) comprises modifying the material with amino gp.-contg. cpds. (II) and then dyeing with a fibre-reactive dispersion dye in supercritical CO₂. Most pref. (I) are, e.g. 2-oxo-1,3-oxazolidine and corresp. derivs. thereof substd. with 4- or 5-aminomethyl or with 4- or 5-(trimethylammonium-methyl) gps. (chloride salt in the latter type) (5 cpds. listed), or 1-(trimethylammonium-methyl)-ethylene carbonate chloride. PREFERRED PROCESS - Dyeing is carried out at 70-200 (pref. 100-150) degrees C for cellulose fibre and 130-210 (pref. 130-150) degrees C for cellulose/polyester, with a CO₂ pressure of 30-400 (pref. 140-250) bar.

IPC 1-7

D06P 3/854; **D06P 5/00**

IPC 8 full level

D06P 3/52 (2006.01); **D06P 1/94** (2006.01); **D06P 3/60** (2006.01); **D06P 3/66** (2006.01); **D06P 3/82** (2006.01); **D06P 3/854** (2006.01); **D06P 5/20** (2006.01); **D06P 5/22** (2006.01)

CPC (source: EP KR US)

D06P 1/16 (2013.01 - KR); **D06P 1/38** (2013.01 - KR); **D06P 1/94** (2013.01 - EP KR US); **D06P 3/54** (2013.01 - KR); **D06P 3/6033** (2013.01 - KR); **D06P 3/6041** (2013.01 - EP US); **D06P 3/66** (2013.01 - EP US); **D06P 3/8233** (2013.01 - EP US); **D06P 3/854** (2013.01 - KR); **D06P 5/225** (2013.01 - EP US)

Citation (search report)

- [Y] DE 4332219 A1 19940331 - CIBA GEIGY [CH]
- [Y] GB 2259525 A 19930317 - CIBA GEIGY AG [CH] & DE 4030325 A
- [PY] EP 0638686 A1 19950215 - HOECHST AG [DE]
- [DA] EP 0546476 A1 19930616 - HOECHST AG [DE]
- [DA] EP 0580091 A1 19940126 - HOECHST AG [DE]
- [DA] DE 3906724 A1 19900913 - DEUTSCHES TEXTILFORSCHENZENTRUM [DE]
- [Y] SAUS W ET AL: "FAERBEN AUS UEBERKRITISCHEM KOHLENDIOXID DISPERSIONSFARBSTOFFE UND BAUMWOLLGEWEBE", TEXTILVEREDLUNG, vol. 28, no. 3, 1 March 1993 (1993-03-01), pages 38 - 40, XP000348883

Cited by

AT413825B; NL1014395C2; EP1126072A3; US6620211B2

Designated contracting state (EPC)

AT BE CH DE DK ES FR GB IE IT LI NL PT

DOCDB simple family (publication)

EP 0690166 A2 19960103; **EP 0690166 A3 19960501**; BR 9502967 A 19960625; CA 2152896 A1 19951230; CN 1118825 A 19960320; DE 4422707 A1 19960104; JP H0874185 A 19960319; KR 960001332 A 19960125; US 5578088 A 19961126

DOCDB simple family (application)

EP 95109421 A 19950619; BR 9502967 A 19950628; CA 2152896 A 19950628; CN 95107627 A 19950629; DE 4422707 A 19940629; JP 16100695 A 19950627; KR 19950017709 A 19950628; US 49659795 A 19950629