

Title (en)

METAL FIBER WITH OPTIMIZED GEOMETRY FOR REINFORCING CEMENT-BASED MATERIALS

Title (de)

METALLFASER MIT OPTIMIERTER GEOMETRIE ZUR VERSTÄRKUNG VON ZEMENTMATERIALEN

Title (fr)

FIBRE METALLIQUE A GEOMETRIE OPTIMISEE POUR RENFORCEMENT DES MATERIAUX A BASE DE CIMENT

Publication

EP 0725871 A1 19960814 (EN)

Application

EP 95915725 A 19950421

Priority

- CA 9500225 W 19950421
- CA 2131212 A 19940831

Abstract (en)

[origin: WO9606995A1] A metal fiber (10) for reinforcing cement-based materials comprises an elongated, substantially straight central portion (12) and sinusoid shaped end portions (14, 14'). The sinusoid at each end portion (14, 14') has an optimum amplitude Ao,opt defined by: $Ao,opt = [k1(\sigma_c)^{<2>} [\sigma_u \alpha \epsilon_f]^{<2>} / (Af/Pf)]$, where $k1 = 2.025 \times 10^{<-2>}$, σ_c = compressive strength of the cement-based material in MPa, $k2 = 3.19 \times 10^{<-1>}$, σ_u = ultimate tensile strength of the metal in MPa, $\alpha = 6.60 \times 10^{<-1>}$, ϵ_f = ductility of the metal in percent, and $\beta = 3.20 \times 10^{<-1>}$, Af = cross-sectional area of the fiber in mm², and Pf = perimeter of the fiber in mm. The sinusoid further has a wavelength Ls defined by: $Ls = (Lf - Lm)/2$, where Lf = length of the fiber, Lm = length of the central portion, and wherein $0.5 Lf < Lm < 0.75 Lf$. Since the optimum amplitude is defined as a function of the ultimate tensile strength and ductility of the fiber material as well as of the compressive strength of the matrix material, it is possible to tailor the fiber geometry according to the properties of the fiber and matrix materials chosen, and ultimately to the composite toughness desired in an actual structure.

IPC 1-7

E04C 5/01

IPC 8 full level

E04C 5/01 (2006.01)

CPC (source: EP KR)

E04C 5/01 (2013.01 - KR); **E04C 5/012** (2013.01 - EP)

Designated contracting state (EPC)

AT BE CH DE DK ES FR GB GR IE IT LI LU MC NL PT SE

DOCDB simple family (publication)

WO 9606995 A1 19960307; AT E194198 T1 20000715; AU 2251795 A 19960322; AU 688031 B2 19980305; CA 2131212 C 19961126; DE 69517668 D1 20000803; DE 69517668 T2 20010222; DK 0725871 T3 20001106; EP 0725871 A1 19960814; EP 0725871 B1 20000628; ES 2151059 T3 20001216; KR 100353732 B1 20030124; KR 960706001 A 19961108; MX 192955 B 19990810; MX 9601504 A 19980630

DOCDB simple family (application)

CA 9500225 W 19950421; AT 95915725 T 19950421; AU 2251795 A 19950421; CA 2131212 A 19940831; DE 69517668 T 19950421; DK 95915725 T 19950421; EP 95915725 A 19950421; ES 95915725 T 19950421; KR 19960702073 A 19960423; KR 19967002073 A 19960423; MX 9601504 A 19960422