

Title (en)

A magnetic steel sheet having excellent magnetic characteristics and blanking performance

Title (de)

Elektroblech mit verbesserten magnetischen Eigenschaften und verbesserter Stanzbarkeit

Title (fr)

Tôle d'acier magnétique ayant des propriétés magnétiques améliorées et ayant une aptitude améliorée à l'estampage

Publication

EP 0741191 A3 19971029 (EN)

Application

EP 96106835 A 19960430

Priority

JP 10848395 A 19950502

Abstract (en)

[origin: US5714017A] A magnetic steel sheet containing, on a weight basis, 0.2 to 6.5% of Si and 0.03 to 2.5% of Mn, having a crystallographic texture wherein the density of aggregation of {100} planes parallel to the surface of the sheet is not less than 10 times that of non-oriented crystal grains, and having a demanganized layer in which the concentration of manganese decreases from the interior of the sheet toward the surface of the sheet, wherein the ratio between the concentration of manganese in the surface portion of the sheet and that in the mid depth portion of the sheet is not more than 0.90 and wherein the maximum ratio of reduction in the concentration of manganese within the demanganized layer is not more than 0.05 wt %/ μm. Magnetic characteristics of the magnetic steel sheet improved by adopting the average grain diameter 0.25 to 10 times the thickness of the sheet and by applying to the sheet a tension smaller than the elastic limit of the sheet in a direction parallel to the surface of the sheet. By employing an appropriate ratio of reduction in the Mn concentration, a relatively high magnetic flux density is obtained without a sharp increase in magnetic flux density, and core loss reduces, thereby providing a non-oriented or doubly oriented magnetic steel sheet having excellent magnetic characteristics and blanking performance.

IPC 1-7

C21D 8/12; **H01F 1/147**

IPC 8 full level

C21D 3/00 (2006.01); **C21D 8/12** (2006.01); **H01F 1/147** (2006.01); **C21D 3/04** (2006.01)

CPC (source: EP KR US)

C21D 3/00 (2013.01 - EP US); **C21D 8/12** (2013.01 - KR); **C21D 8/1255** (2013.01 - EP US); **C22C 38/00** (2013.01 - KR); **C22C 38/04** (2013.01 - KR); **H01F 1/047** (2013.01 - KR); **H01F 1/14775** (2013.01 - EP US); **C21D 3/04** (2013.01 - EP US); **C21D 8/1272** (2013.01 - EP US); **C21D 8/1283** (2013.01 - EP US); **Y10T 428/12458** (2015.01 - EP US)

Citation (search report)

- [AD] JP S5331515 A 19780324 - KAWASAKI STEEL CO & DATABASE WPI Section Ch Week 7818, Derwent World Patents Index; Class M21, AN 78-32872A
- [AD] JP H01108345 A 19890425 - SUMITOMO METAL IND & PATENT ABSTRACTS OF JAPAN vol. 013, no. 331 (C - 622) 25 July 1989 (1989-07-25)
- [XP] WO 9512691 A1 19950511 - SUMITOMO METAL IND [JP], et al & JP H07173542 A 19950711 - SUMITOMO METAL IND
- [A] EP 0613957 A1 19940907 - DRESDEN EV INST FESTKOEPRER [DE]
- [A] EP 0431502 A2 19910612 - EBG ELEKTROMAGNET WERKSTOFFE [DE]
- [A] EP 0318051 A2 19890531 - NIPPON STEEL CORP [JP]
- [A] EP 0206108 A2 19861230 - NISSHIN STEEL CO LTD [JP]
- [X] T. TOMIDA ET AL.: "Development of (100) Texture in Silicon Steel", ISIJ INTERNATIONAL, vol. 35, no. 5, 1995, TOKYO, JP, pages 548 - 556, XP002038748 & TETSU-TO-HAGANÉ, vol. 79, 1993, TOKYO, JP, pages 1350 - ?

Cited by

CN103649345A; RU2688348C2; KR102283222B1; KR102376026B1; KR102417226B1; KR102283217B1; KR102296376B1; TWI479032B; KR102283225B1; WO2022234902A1

Designated contracting state (EPC)

DE FR GB

DOCDB simple family (publication)

US 5714017 A 19980203; CA 2175401 A1 19961103; CA 2175401 C 19990831; DE 69625845 D1 20030227; DE 69625845 T2 20031224; EP 0741191 A2 19961106; EP 0741191 A3 19971029; EP 0741191 B1 20030122; KR 100224283 B1 19991015; KR 960041389 A 19961219

DOCDB simple family (application)

US 64005496 A 19960430; CA 2175401 A 19960430; DE 69625845 T 19960430; EP 96106835 A 19960430; KR 19960014130 A 19960501